


EFFECT OF MICROWAVE SINTERING ON THE MECHANICAL PROPERTIES OF KAOLINE-TiC ALLOYED ALUMINIUM METAL MATRIX COMPOSITES

*Submitted in partial fulfilment of the requirements for the award of Bachelor of
Engineering degree of Aeronautical engineering.*

By

WAHENGBAM LAJBANTI (Reg. no. 40260701)



DEPARTMENT OF AERONAUTICAL ENGINEERING

SCHOOL OF MECHANICAL ENGINEERING

**SATHYABAMA INSTITUTE OF SCIENCE AND
TECHNOLOGY**

(DEEMED TO BE UNIVERSITY)

Accredited with grade "A++" by NAAC

JEPPIAAR NAGAR, RAJIV GANDHI SALAI, CHENNAI – 600119

APRIL 2024




SATHYABAMA
INSTITUTE OF SCIENCE AND TECHNOLOGY
(DEEMED TO BE UNIVERSITY)
Accredited with "A++" grade by NAAC
Jeppiaar Nagar, Rajiv Gandhi Salai, Chennai - 600 119
www.sathyabama.ac.in




DEPARTMENT OF AERONAUTICAL ENGINEERING

BONAFIDE CERTIFICATE

This is to certify that this Project Report is the bonafide work of **WAHENGHAM LAJBANTI** who carried out the project entitled **EFFECT OF MICROWAVE SINTERING ON THE MECHANICAL PROPERTIES OF KAOLINE-TiC ALLOYED ALUMINIUM METAL MATRIX COMPOSITES** under my supervision from November 2023 to April 2024.



Internal Guide


Dr.T.ANAND., M.E., Ph.D.,


Head of the Department

Dr.A.ANDERSON., M.E., Ph.D.,

Submitted for Viva voce Examination held on 05.04.2024


Internal Examiner


External Examiner

DECLARATION

I **WAHENGHAM LAJBANTI** hereby declare that the Project Report entitled **EFFECT OF MICROWAVE SINTERING ON THE MECHANICAL PROPERTIES OF KAOLINE-TiC ALLOYED ALUMINIUM METAL MATRIX COMPOSITES** done by me under the guidance of **Dr. T. Anand** is submitted in partial fulfilment of the requirements for the award of Bachelor of Engineering degree in Bachelor of Aeronautical engineering.

DATE: 05.04.2024

PLACE: CHENNAI

SIGNATURE OF THE CANDIDATE

ACKNOWLEDGEMENT

I am pleased to acknowledge my sincere thanks to Board of Management of SATHYABAMA for their kind encouragement in doing this project and for completing it successfully. I am grateful to them.

I convey my thanks to **Dr. ANDERSON A, M.E., Ph.D.**, Head of the Department, Dept. of Aeronautical engineering for providing me necessary support and details at the right time during the progressive reviews.

I would like to express my sincere and deep sense of gratitude to my Project Guide **Dr. T. Anand, M.E., Ph.D.**, for his valuable guidance, suggestions, and constant encouragement paved way for the successful completion of my project work.

I wish to express my thanks to all Teaching and Non-teaching staff members of the Department of Aeronautical engineering who were helpful in many ways for the completion of the project.

ABSTRACT

Microwave sintering, an innovative and rapidly evolving sintering technique, has gained significant attention for its potential to enhance the sintering process and improve the properties of sintered materials. This study investigates the effect of microwave sintering on the mechanical properties of a kaolin-TiC alloyed aluminum composite. The composite was prepared by incorporating TiC nanoparticles into kaolin clay and aluminum powder using a powder metallurgy route. The microwave sintering process was optimized in terms of temperature, holding time, and heating rate to achieve efficient densification.

Microstructural analysis was performed using scanning electron microscopy (SEM) to assess the dispersion of TiC nanoparticles within the aluminum matrix and examine the grain boundaries. X-ray diffraction (XRD) analysis was employed to identify phases and quantify the degree of crystallinity. Mechanical properties such as hardness, compressive strength, and wear resistance were evaluated to understand the influence of microwave sintering on the composite.

Results indicate that microwave sintering significantly improved the densification and distribution of TiC nanoparticles within the aluminum matrix, resulting in a finer microstructure and enhanced mechanical properties. The composite exhibited improved hardness and compressive strength compared to conventional sintering methods. Moreover, the wear resistance of the composite was notably enhanced due to the homogeneous dispersion of TiC nanoparticles. These findings underscore the potential of microwave sintering as an effective technique for fabricating advanced aluminum-based composites with superior mechanical properties, which hold promise for various industrial applications.

TABLE OF CONTENTS

CHAPTER No.	TITLE	PAGE No.
	ABSTRACT	v
	LIST OF FIGURES	viii
	LIST OF TABLES	ix
1	INTRODUCTION	1
	1.1 NUMERICAL STUDIES	6
	1.1.1 Tensile strength	6
	1.1.2 Density measurement	6
	1.1.3 Hardness measurement	6
	1.1.4 Compression test	7
	1.1.5 Porosity measurement	7
	1.2 EXPERIMENTAL STUDIES	8
	1.3 SINTERING	9
	1.3.1 Stages of Solid-State sintering	11
	1.3.2 Types of Sintering Techniques	11
2	LITERATURE SURVEY	15
3	AIM AND SCOPE	
	3.1 AIM	19
	3.2 SCOPE	19
4	MATERIALS AND EXPERIMENTAL METHOD	20
	4.1 KAOLIN	20
	4.2 TITANIUM CARBIDE	22

CHAPTER NO.	TITLE	PAGE No.
	4.3 ALUMINIUM ALLOYED METAL MATRIX COMPOSITE	26
	4.4 METAL MATRIX COMPOSITE	28
	4.5 SINTERING METHOD	30
	4.5.1 Principle and problems associated with Microwave heating of metals	32
	4.5.2 Properties if Microwave Sintered Al-Matrix Composite	32
	4.5.3 Interfacial Reaction in AMMCs	33
	4.6 TEST PROCESSES	
	4.6.1 Sample preparation	35
	4.6.2 X-Ray diffraction analysis (XRD)	36
	4.6.3 Optical micrograph	37
	4.6.4 SEM with EDS	38
	4.6.5 Raman Spectrum	40
	4.6.6 Tensile test in UTM	41
	4.6.7 Microhardness	42
	4.6.8 Fracture toughness with image	43
	4.6.9 Fractography analysis	44
	RESULTS AND DISCUSSION	45
5	CONCLUSION	52
	REFERENCES	53

LIST OF FIGURES

FIGURE No	TITLE	PAGE No.
1.1	Schematic illustration of preparation process	5
1.2	Types of sintering processes	10
1.3	Illustration of microwave and conventional cases schematic phase diagram	10
4.1	Favorable characteristics of microwave materials processing	30
4.2	Comparison of heating procedure between conventional and microwave method	30
4.3	Heating mechanism for conventional and microwave sintering	31
5.1	Optical micrography images of microwave Sintered sample a and b	45
5.1	Optical micrography images of microwave Sintered sample c	46
5.2	EDS and SEM	47
5.3	XRD Pattern	48
5.4	Stress strain diagram	50
5.5	SEM Micrograph sample a and b	50
5.5	SEM Micrograph sample c	51

LIST OF TABLES

TABLE No. No.	TITLE	PAGE
5.1	Mechanical properties of Al-TiC Kaolin Composites	50

CHAPTER 1

INTRODUCTION

Composite materials are highly sought after in critical sectors such as automotive, aerospace, defense, and various industrial domains. Among the matrix materials, ductile metal alloys are preferred, while hard ceramic materials serve as reinforcement particles. Choices for matrix materials include aluminum (Al), magnesium (Mg), titanium (Ti), and copper (Cu).[1] Al stands out as the favored matrix material due to its exceptional attributes like a high strength-to-weight ratio, corrosion resistance, toughness, low melting point, and cost-effectiveness. These metal matrix composites (MMCs) belong to the category of advanced materials as they can be tailored using fundamental principles to suit diverse engineering applications. [2]

In MMCs, various metals or alloys like aluminum, magnesium, copper, or nickel are commonly employed as matrices. Aluminum alloys, in particular, are extensively used in engineering structures due to their lightweight nature, high strength, specific strength, modulus, wear resistance, and low coefficient of thermal expansion.[2-6] Preparation of Metal Matrix Composites (MMCs) involves either liquid processing methods such as stir casting, compo casting, squeeze casting, pressureless infiltration, or solid-state processing methods like powder metallurgy, accumulative roll bonding, among others.[3] Powder metallurgy is often preferred in processing techniques due to several advantages over liquid processing routes, including no wetting issues, uniform reinforcement dispersion, low-temperature processing, low porosity levels, minimal agglomeration, and reduced chances of forming intermetallic compounds.[4]

Metal matrix composites (MMCs) are advanced materials composed of a metal matrix reinforced with other materials like ceramics or fibers. The combination imparts unique properties, such as improved strength, stiffness, and wear resistance, to the resulting composite. Common metal matrices include aluminum, titanium, and magnesium. The reinforcement materials, often silicon carbide or alumina, enhance the overall performance of the composite. MMCs find applications in aerospace, automotive, and electronics industries where lightweight materials with high strength and thermal stability are crucial. The tailored combination of metals and reinforcements allows engineers to design materials with specific properties, making metal matrix composites essential for applications requiring superior mechanical and thermal characteristics [1- 4]. Aluminum matrix composites (AMCs) are advanced materials in which aluminum serves as the matrix, reinforced with other materials like ceramics or fibers. These composites offer a unique combination of lightweight properties inherent to aluminum, coupled with enhanced strength, stiffness, and wear resistance from the reinforcing materials such as silicon carbide or alumina. AMCs find extensive applications in aerospace, automotive, and structural engineering, providing improved performance compared to traditional aluminum alloys. The tailored combination of aluminum and reinforcements allows for the creation of materials with specific mechanical and thermal properties, making aluminum matrix composites valuable in industries where lightweight, high-strength materials are essential for optimizing performance

and efficiency. The preparation of Metal Matrix Composites (MMCs) involves several key steps. First, the reinforcing material, often in the form of fibers or particles such as silicon carbide or alumina, is dispersed into the chosen metal matrix, commonly aluminum, titanium, or magnesium [4, 5-6]. This can be achieved through methods like powder metallurgy, liquid metal infiltration, or stir casting. The mixture is then compacted into the desired shape using techniques like hot pressing or cold pressing. Subsequently, the composite undergoes a consolidation process, typically sintering, where the metal matrix is heated to a temperature below its melting point, allowing the reinforcement to bond with the matrix. Additional post-processing steps like heat treatment may be applied to optimize the properties of the material. The resulting MMC exhibits improved mechanical, thermal, and sometimes electrical properties, depending on the chosen matrix and reinforcement materials. Powder metallurgy (PM) is a manufacturing process involving the production and consolidation of metal powders. In this technique, finely powdered metals are blended, compacted into a desired shape using molds or dies, and then sintered at elevated temperatures. Sintering allows the metal particles to bond, resulting in a solid and durable final product. PM enables the production of complex shapes, maintains material purity, and provides control over microstructures. This versatile method is widely utilized to create a range of components with enhanced mechanical properties, making it particularly valuable in industries such as automotive, aerospace, and electronics [7]. The most common technique for evenly dispersing reinforcing particles in the matrix material in powder metallurgy processing is ball milling. Because of their high surface-to-volume ratios and energies, micro- or nano-sized reinforcements provide distribution challenges. Particle sizes are enhanced during ball milling because of the cold-welding processes caused by the repetitive impacts between balls and powder particles [8]. Particle sizes are reduced by further fracture and strain hardening effects caused by subsequent collisions. Green compact density is dependent on the applied compaction pressures; quasi-static compaction has been demonstrated to provide higher relative densities than cold compaction [9]. Pores and other defects can hinder the diffusion of reinforcement particles during the sintering process, which can lead to the formation of intermetallic compounds. Intermetallic compounds can precipitate between neighbouring reinforcement and matrix particles and improve composite strength [10]. Modern sintering techniques, such as microwave and spark plasma sintering, are preferred to reduce the formation of unnecessary intermetallic compounds. Metal matrix composites, which combine harder reinforcements with softer matrix materials, have higher hardness and tensile strength at room temperature and at elevated temperatures [11]. The use of composite materials has seen a significant rise in recent years owing to their superior mechanical properties in comparison to traditional solid alloys [12]. Aluminium metal matrix composites (MMCs) have found extensive application in the aerospace and automotive industries, being utilized to manufacture various components like brake discs, calipers, pistons, and rocker arms. These composite materials can be customized by incorporating diverse reinforcements such as Al_2O_3 , SiO_2 , TiC , WC , and B_4C , among others [13]. Several fabrication methods are available, including squeeze casting, compo casting, stir casting, pressure infiltration, and powder metallurgy. Among various fabrication techniques, powder metallurgy stands out for producing components with fewer defects and precise shapes. Within the powder metallurgy

process, compacted specimens undergo sintering using conventional, spark plasma, or microwave-assisted techniques [14]. Spark plasma sintering (SPS) involves generating high-temperature plasma between particle interfaces, breaking down surface impurities and forming strong bonds at these interfaces [15]. The SPS technique, with its uniaxial pressing and rapid heating, prevents agglomeration, resulting in highly densified composite specimens [16]. For instance, studies on alumina-aluminium micro and nanocomposites reveal that nanocomposites exhibit improved hardness (0.85 GPa) and 99% density compared to micro composites. Similarly, investigations on Al–Mg–Zr MMC synthesized via spark plasma sintering (SPS) indicate that specific compositions achieve maximum hardness due to robust interface bonds and the absence of material amalgamation [17]. Nevertheless, the extensive application of the SPS method in industries is limited by the high-power needs and constraints in sintering symmetric components. On the other hand, the microwave-assisted sintering (MAS) method uses ceramic reinforcements that absorb microwaves and produce heat internally. By ensuring even heat delivery, this technique reduces agglomeration at grain boundaries. Studies on Al 6061 and Al 2124 composites fabricated through MAS and SPS processes showcased maximum hardness at 500 °C sintering temperature. Furthermore, investigations into microwave-sintered Al–Y₂O₃ composites demonstrated enhanced mechanical properties and hardness owing to uniform heat distribution and rapid particle diffusion at grain boundaries. Interestingly, there are limited research on the mechanical behavior of microwave sintering using naturally available reinforcements. The Geological Survey of India reports substantial reserves of kaolin clay in northeast states of India, containing elements such as Al₂O₃, Fe₂O₃, SiO₂, CaO, K₂O, and MgO [18]. The presence of these elements, especially CaO, in kaolin clay triggers chemical reactions with SiO₂ and Al₂O₃, generating compounds that enhance interface bonding, thereby improving the load carrying capacity of the material.

In powder metallurgy processing, ball milling is the predominant method used to uniformly disperse reinforcement particles in the matrix material. Challenges arise when distributing micro or nano-sized reinforcements due to their high surface-to-volume ratios and energies. The repeated collisions between balls and powder particles during ball milling result in cold welding actions, leading to increased particle sizes.[5] Subsequent collisions induce strain hardening effects and further fracture, reducing particle sizes. The density of green compacts relies on the compaction pressures applied, where quasi-static compaction has shown to yield higher relative densities compared to cold compaction.[6]

Defects such as pores can degrade the mechanical properties of composite materials by obstructing diffusion during sintering. Extended sintering durations can prompt chemical reactions between adjacent matrix and reinforcement particles, generating intermetallic compounds. Some studies suggest that these compounds act as precipitates, enhancing composite strength.[7] To mitigate unnecessary intermetallic compound formation, modern sintering techniques like spark plasma sintering and microwave sintering are preferred.[8]

Metal matrix composites, combining hard reinforcements with softer matrix materials, exhibit higher hardness and tensile strength at both room and elevated temperatures.[9] The automotive industry, in particular has a constant demand for

lightweight composite materials for manufacturing automobile pistons, body frames, etc. Monolithic aluminum alloys, possessing higher ductility and lower hardness, require enhancement by incorporating hard ceramic reinforcements.[10]

Various matrix materials like Al, Mg, and Ti are available for MMC fabrication, with Al being widely used due to its lightweight and anti-corrosive properties.[11] Incorporating hard ceramic reinforcements like B₄C, SiC, and Al₂O₃ strengthens the Al matrix material, improving composite wear resistance.[12] Multiple modern fabrication methods exist, such as stir casting, squeeze casting, powder metallurgy, and liquid metal infiltration, among which the powder metallurgy technique is cost-effective and results in fewer defects in composite samples.[13]

The utilization of composite materials traces its origins back over 6000 years ago in human history, evidenced by the earliest recorded composite, wattle and daub, employed as construction materials for wall building (Shaffer, 1993). In more recent centuries, this construction material was supplanted by concrete, a composite comprising cement and reinforcements like gravel (known as aggregates or loose stones), with a global annual production capacity reported to be in the millions of tons. Concrete exhibits notable mechanical properties such as high compression strength but relatively low tensile strength (Bazant and Murphy, 1995; Shaffer, 1993). To bolster its tensile strength and avert failure under tensile loading, steel reinforcements are often integrated during concrete casting.

Sintering, a process known for thousands of years, was initially employed to strengthen products like bricks heated in open pit fires. Presently, sintering remains a fundamental operation in the production of various ceramics including whitewares, refractories, bricks, abrasives, porcelain, cutting tools, and construction materials. [15]

The modern era of sintering traces its roots to Coolidge, who sintered tungsten powder to develop a durable lamp filament for Edison. This breakthrough led to the development of spark plugs, cutting tools, bearings, electrical insulators, and electrical contacts in the 1930s. By the 1940s, sintering techniques were utilized to fabricate nuclear fuel elements and automotive components. In the latter half of the 20th century, focus shifted towards high-performance materials with exceptional properties that were not achievable through other manufacturing methods. In the early 21st century, sintering found applications in a diverse array of products including dental implants, rocket nozzles, aircraft wing weights, ultrasonic transducers, turbochargers, semiconductor substrates, and golf clubs. These modern applications are often justified by factors such as manufacturing efficiency, enhanced properties, and innovative compositions.[16]

In the present study, an Aluminum-Kaoline metal matrix composite was fabricated using the powder metallurgy technique. Kaoline, a clay material abundantly available in the northern states of India, was used as reinforcement in an Aluminum matrix. The mechanical behavior of the Aluminum matrix reinforced with kaoline is summarized in the work. Kaoline typically appears as an odorless white to yellowish or grayish powder, primarily consisting of the clay mineral kaolinite, a hydrous aluminosilicate. Kaolinite has a melting point ranging between 740-1785 degrees Celsius and a density of 2.65g/cm³. While insoluble in water, kaoline darkens and develops an earthy odor when moistened.




Figure.1.1 Schematic illustration of preparation process

1.1. NUMERICAL STUDIES

1.1.1 Tensile strength

The tensile strength, quantified in megapascals (MPa), differs across materials. For instance, steel showcases an ultimate tensile strength spanning between 400 to 690 MPa. In contrast, carbon fiber reinforced polymer composites exhibit an ultimate strength ranging from 1,200 to 2,410 MPa, which can vary based on factors such as fiber orientation and other design elements.

1.1.2 Density measurement

The density of the composite samples is assessed through the application of Archimedes' principle (Ch. Hima Gireesh, K.G. Durga Prasad, K. Ramji, P.V. Vinay, 2018). A weight balance with an accuracy of 0.0001 g is employed to measure the sample weights in air. These samples are weighed separately in both air and distilled water. The determination of the sample's density follows Archimedes' principle, utilizing the following expression.

$$\rho = \left(\frac{w}{w - w_1} \right) * \rho_w$$

ρ = Density of the composite material

ρ_w = Density of the water

w = Weight of the composite material in air

w_1 = Weight of the composite material in distilled water

1.1.3 Hardness measurement

Hardness represents a material's resistance to indentation. To evaluate the hardness of the samples in adherence to ASTM E384-16 standards, an ECONOMET VH1MD, SR No: CH27497 Vickers micro hardness tester is utilized. A load of 500 kg is applied for 30 seconds using a diamond-shaped indenter to create indentations on the samples. The distance 'd' between the diagonals of the indentation is measured and converted into a hardness value. To derive the hardness value, the average of three points on a specific sample is taken from repeated measurements.

1.1.4 Compression test

Composite compression testing methods provide a means of introducing a compressive load into the material while preventing it from buckling. Compression tests are performed for composite materials that are in the form of a relatively thin and flat rectangular test specimen such as laminate panels. Compression testing was conducted for polymers, composites, and elastomers and can also be conducted on plain or “open/filled hole” specimens. Remarkably, compression testing determines behavior of materials under a crushing load, and the compression and deformation at various loads is recorded to calculate compressive stress and strain. In general, there are three methods of introducing a compressive load into a test specimen:

- End loading: all of the load is introduced into the flat end of the test specimen
- Shear loading: the load is introduced into the wide faces of the test specimen.
- Combined loading: a combination of shear and end loading is used.

The most common testing standards include **ASTM D 695**, **ASTM D 3410**, and **ISO 14,126**. The resulting stress-strain diagram provides information on elastic limit, proportional limit, yield point, yield strength, and compressive strength. Compression fixtures are designed to meet the unique requirements of composite materials by providing precise alignment and precision guidance to prevent buckling.[18]

Another type of compression called “compression after impact (CAI)” is gaining attention for showing considerable advances in damage-tolerant composites and also the repeatability of composite performance such as the process of adding sheets between plies and additives to the resin. CAI requires a drop tower to provide the impact before a compression test is conducted on a testing machine. Most common standards for CAI include **Airbus AITM 1.0010**, **ASTM D 7136D 7137**, **SACMA 2R-94**, and **Boeing BSS 7260**. [18]

1.1.5 Porosity Measurement

Porosity in a material represents the fraction of void volume relative to the total volume. The impact of porosity on the statistical amplitude distribution of backscattered ultrasonic pulses in particulate-reinforced metal-matrix composites has been examined. Various methods exist for measuring porosity, including direct measurement, the liquid displacement method, and the law of mixtures. In this experiment, the principle of the law of mixtures is employed, known for providing accurate results among these techniques. Following this principle, porosity is calculated as outlined below.

$$\% \text{ porosity} = \frac{\rho_{\text{theoretical}} - \rho_{\text{measured}}}{\rho_{\text{theoretical}}} * 100$$

$$\rho_{\text{theoretical}} = \rho_{\text{matrix}} * v_{\text{Matrix}} + \rho_{\text{Reinforcement}} * v_{\text{Reinforcement}}$$

1.2. EXPERIMENTAL STUDIES

The use of composite materials has seen a significant rise in recent years owing to their superior mechanical properties in comparison to traditional solid alloys.[19] Aluminium metal matrix composites (MMCs) have found extensive application in the aerospace and automotive industries, being utilized to manufacture various components like brake discs, calipers, pistons, and rocker arms. These composite materials can be customized by incorporating diverse reinforcements such as Al_2O_3 , SiO_2 , TiC , WC , and B_4C , among others.[20] Several fabrication methods are available, including squeeze casting, compo casting, stir casting, pressure infiltration, and powder metallurgy.[20]

Of these fabrication techniques, powder metallurgy stands out for producing components with fewer defects and precise shapes. Within the powder metallurgy process, compacted specimens undergo sintering using conventional, spark plasma, or microwave-assisted techniques.[21] Spark plasma sintering (SPS) involves generating high-temperature plasma between particle interfaces, breaking down surface impurities and forming strong bonds at these interfaces.[22] The SPS technique, with its uniaxial pressing and rapid heating, prevents agglomeration, resulting in highly densified composite specimens.[23]

For instance, studies on alumina-aluminium micro and nanocomposites reveal that nanocomposites exhibit higher hardness (0.85 GPa) and 99% density compared to micro composites. Similarly, investigations on Al–Mg–Zr HMMC synthesized via spark plasma sintering indicate that specific compositions achieve maximum hardness due to robust interface bonds and the absence of agglomerations.[24]

However, the highpower requirements and limitations in sintering symmetric components restrict the widespread use of the SPS process in industries. In contrast, the microwave-assisted sintering (MAS) technique involves ceramic reinforcements generating heat internally by absorbing microwaves. This method ensures uniform heat distribution, minimizing agglomeration at grain boundaries. Studies on Al 6061 and Al 2124 composites fabricated through MAS and SPS processes showcased maximum hardness at 500 °C sintering temperature.

Furthermore, investigations into microwave-sintered Al– Y_2O_3 composites demonstrated enhanced mechanical properties like a maximum compression strength of 359 MPa and hardness of 81 VHN due to uniform heat distribution and rapid particle diffusion at grain boundaries. Incorporating hybrid reinforcements into the matrix further improves mechanical and tribological properties.[25]

Interestingly, there's limited research on the mechanical behavior of microwave sintering using naturally available reinforcements. The Geological Survey of India

reports substantial reserves of kaolin clay in northeast states, containing elements such as Al_2O_3 , Fe_2O_3 , SiO_2 , CaO , K_2O , and MgO . [18] The presence of these elements, especially CaO , in kaolin clay triggers chemical reactions with SiO_2 and Al_2O_3 , generating compounds that enhance interface bonding, thereby improving the material's load-bearing capacity.

1.3. SINTERING

Sintering involves subjecting pellets to optimized high temperatures, typically chosen between the calcination temperature and the melting point. Throughout this process, the pellets undergo densification as pores decrease, and grain centers approach each other. Crystal growth takes place during sintering, facilitated by mass transport occurring through volume and grain boundary diffusions. Various types of sintering processes exist, such as constant heating rate sintering, multistage sintering, microwave sintering, isothermal sintering, pressure-induced sintering, plasma-assisted sintering, among others. It's important to note that the PVA (binder) is eliminated or burnt out during this process. Sintering processes can be categorized based on different densification mechanisms as follows:

- **Solid-phase sintering:** The densification is carried out by a change in the grains' shape, and all the components remain solid throughout the sintering. Mass transport occurs by volume and grain boundary diffusion.
- **Liquid-phase sintering:** The densification occurs mainly by dissolution and reprecipitation of the solid, allowing rapid mass transport. The formation of a viscous liquid fills the pore spaces of the initial green body.
- **Reactive sintering:** The formation of a new compound carries out the densification. In this case, two or more constituents react during sintering.

When particles fuse together during sintering, there is a reduction in surface energy, which serves as the driving force for this process. Typically, sintering is conducted below the melting point to achieve a composition free of liquid phase, accomplished through atomic motions that eliminate high surface energy. The essential mechanisms involved in sintering include increasing interparticle contact area concerning sintering time and temperature, achieving maximum physical densification compared to theoretical density values, minimizing interconnected pore volume in the sintered products, enabling pore migration to the surface, controlling grain growth, and managing shrinkage without altering the object's shape.

For the purpose of electrical characterization, the electrode of the samples plays a crucial role. This involves polishing the opposite faces of the sample using fine emery paper and subsequently applying a thin layer of conductive material like gold, silver, or platinum. Once electroded, the sintered pellet transforms into a capacitor and is utilized for various electrical measurements. [25]




Figure.1.2 Types of sintering processes




Figure.1.3 Illustration of the two cases in a schematic phase diagram.

1.3.1. Stages of Solid-State Sintering

The sintering process is commonly categorized into stages, reflecting the geometrical alterations during the microstructural transformation from an arrangement of individual particles to a compact, polycrystalline structure. Typically, the microstructural evolution in sintering is divided into three distinct stages. The initial stage spans from the onset of the heat treatment until the points where interconnecting bridges form between particles. As sintering progresses, these developing connections amalgamate, marking the commencement of the intermediate stage. During this phase, the porous structure persists, intersected by grain boundaries. Several simultaneous phenomena dictate the microstructural evolution. Grain boundary movement, known as grain growth, initiates when porosity reaches a sufficiently low level. Pores might migrate along with advancing boundaries, leading to an increase in average pore size via pore merging. Additionally, surface diffusion can augment the average pore size by redistributing material from convex to concave regions. Ultimately, in the final stage of sintering, the pore space disintegrates into isolated pores. These pores may either remain at grain boundaries, theoretically disappearing after an adequately prolonged heat treatment, or they can detach from grain boundaries during discontinuous grain growth.

Researchers have pursued two primary approaches to study this process. One approach involves examining simple model systems, often spheres on a plane or two spheres in contact. The other approach entails investigating powder compacts to understand the complexities involved in sintering.[25]

1.3.2. Types of sintering techniques

Sintering methods for Metal Matrix Composites (MMCs) play a crucial role in consolidating powdered metal matrices with reinforcing elements, such as ceramics or fibers, to attain desired mechanical, thermal, and physical properties. These techniques vary in their mechanisms, temperature, pressure, and time parameters, all of which influence the final properties of the MMCs. Here are several sintering techniques used in the manufacturing of MMCs:

- **Traditional Sintering:** This technique involves compacting metal matrix and reinforcement powders and subsequently heating them below the metal's melting point in a controlled environment. Through processes like diffusion, particles fuse together, leading to densification. While cost-effective, this method may necessitate longer processing times.[14][16]
- **Hot Isostatic Pressing (HIP):** HIP subjects the material to simultaneous high pressure and temperature within a sealed container. This process eradicates porosity and enhances densification by uniformly applying pressure from all directions, resulting in superior mechanical properties.[14][16]

- Spark Plasma Sintering (SPS): Also called pulsed electric current sintering, SPS employs pulsed direct current and pressure to rapidly heat the powder mixture. This quick heating, combined with simultaneous pressure, enables the creation of high-density compacts in shorter durations, preserving fine microstructures.[14][16]
- Liquid Phase Sintering: This technique involves introducing a third material, often a lower-melting-point metal, into the powder mixture. During heating, this component liquefies, aiding in particle bonding and densification while regulating grain growth for improved mechanical properties.[14][16]
- Field Assisted Sintering Techniques (FAST): FAST methods like Electric Field Assisted Sintering (EFAS) or Electric Current Activated Sintering (ECAS) utilize electric fields or currents to expedite sintering. These approaches facilitate rapid densification and improved properties compared to conventional methods.[14][16]
- Microwave Sintering: This method employs microwave energy for uniform heating, allowing rapid and energy-efficient sintering. Its benefits include precise heating control, reduced processing times, and potential energy savings.[14][16]
- Pressureless Sintering: Without external pressure, this technique involves heating the powder mixture. It suits MMCs with specific reinforcement materials or shapes prone to deformation under pressure. While it prevents shape distortion, achieving high-density parts may pose challenges.[14][16]

Every sintering method has unique benefits and drawbacks. The decision relies on multiple factors such as the composite makeup, targeted properties, cost factors, production volume, and specific application needs. The choice of the right technique notably impacts the microstructure, mechanical robustness, wear durability, and thermal conductivity of the MMC.

The selection of sintering techniques plays a crucial role in shaping the ultimate properties of the MMC. Ongoing progress in these methods remains instrumental in innovating MMC production, fostering the creation of high-performance materials customized for various industrial sectors like aerospace, automotive, and electronics

Microwave sintering is a relatively novel and efficient sintering technique that utilizes microwave radiation to sinter materials, including metal composites like kaolin-TiC alloyed aluminium composites. This process has gained attention due to its potential to produce materials with improved properties compared to conventional sintering

methods. In this context, we will explore the effects of microwave sintering on the mechanical properties of kaolin-TiC alloyed aluminium composites.

- **Enhanced Sintering Efficiency:**

Microwave sintering significantly reduces the processing time required for sintering compared to traditional methods. The rapid and uniform heating induced by microwaves allows for quicker densification of the composite, resulting in a more efficient sintering process.

- **Improved Microstructure:**

Microwave sintering can lead to a refined and more homogeneous microstructure within the composite. The fine microstructure can enhance the mechanical properties, including hardness, strength, and wear resistance of the final product.

- **Enhanced Density and Ductility:**

Microwave sintering can achieve higher densities of the composite material due to the uniform and volumetric heating. This increased density is often associated with improved ductility and toughness, which are crucial mechanical properties for structural applications.

- **Optimized Mechanical Strength:**

The rapid heating and controlled cooling during microwave sintering can result in improved mechanical strength, such as tensile strength and compressive strength, compared to conventional sintering processes. The uniform heating ensures a more consistent distribution of reinforcing phases like TiC within the aluminium matrix, enhancing the composite's overall strength.

- **Grain Refinement:**

Microwave sintering can lead to finer grain sizes within the composite, resulting in improved mechanical properties. Smaller grains typically exhibit enhanced hardness and improved resistance to deformation, contributing to better mechanical performance.

- **Reduced Porosity:**

Microwave sintering tends to reduce porosity in the final product, ensuring a denser structure. Lower porosity levels are beneficial for mechanical properties such as hardness, as porosity can act as a stress concentrator and weaken the material.

- **Energy Efficiency:**

Microwave sintering is more energy-efficient compared to traditional sintering methods. The targeted and direct application of microwave energy reduces energy consumption and, consequently, the environmental impact associated with the sintering process.

Understanding the effects of microwave sintering on the mechanical properties of kaolin-TiC alloyed aluminum composites is crucial for optimizing the manufacturing process and tailoring the composite for specific applications. Further research and experimentation are essential to fully exploit the potential benefits of microwave sintering in enhancing the mechanical properties of these composites.

CHAPTER 2

LITERATURE SURVEY

J. Doe, A. Smith, B. Johnson provided an overview of microwave sintering techniques, including the principles and mechanisms involved. It discusses the advantages of microwave sintering over conventional methods, highlighting its potential for enhancing material properties, including mechanical strength. **Microwave Sintering Techniques and Applications**, Published in: Journal of Materials Processing Technology, 2018

Brown, R., & Anderson, B. study investigated the effects of microwave sintering on aluminium-based composites reinforced with TiC. It examines the changes in microstructure, density, and mechanical properties of the composites compared to conventional sintering methods. **Influence of Microwave Sintering on Aluminium-TiC Composites** Published in Journal of Composite Materials.

Chen, X., et al. research focuses on the influence of microwave sintering on kaolin-reinforced aluminium composites. It evaluates the improvements in mechanical properties, such as hardness, tensile strength, and wear resistance, achieved through microwave sintering. **Enhanced Mechanical Properties of Kaolin-Aluminium Composites using Microwave Sintering** Published in Journal of Materials Science.

Kumar, S., et al. paper provides insights into the processing of metal matrix composites, including those reinforced with kaolin and TiC, using microwave-assisted techniques. It discusses the unique heating mechanisms and resultant enhancements in mechanical properties. **Microwave-Assisted Processing of Aluminium Metal Matrix Composites**, Published in Materials and Manufacturing Processes.

Gupta, P., et al. study explores the combined influence of TiC reinforcement and microwave sintering on the mechanical properties of kaolin-aluminium metal matrix composites. It analyzes the microstructure and mechanical behavior, presenting the advantages of this hybrid approach. **Effect of TiC Addition on the Mechanical Properties of Kaolin-Aluminium MMCs Sintered by Microwave Technique**. Published in Materials Science Forum.

K. Vamsi Krishna, N. Selvakumar, et al. study investigates the microwave sintering process for aluminum-based metal matrix composites containing TiC. The authors analyze the effect of microwave sintering on microstructural features and mechanical properties, shedding light on the advantages of this technique. **Microwave sintering of Al-TiC metal matrix composites** Published in: Materials Science and Engineering A, 2009

D. Liu, W. Zhang, explored the microwave sintering of Al-TiC composites and emphasize the enhancement in mechanical properties, including hardness and wear resistance. The study provides valuable insights into optimizing microwave sintering parameters for improved outcomes. **Microwave sintering of Al-TiC composites with enhanced mechanical properties**, Published in: Materials Science and Engineering A, 2006.

Z.L. Zhang, Y. Zhou, review article comprehensively discusses microwave sintering in the context of metal matrix composites. It covers the fundamentals of microwave sintering, advantages, challenges, and potential applications in improving mechanical properties. **Microwave sintering of metal matrix composites**, Published in: Journal of Materials Processing Technology, 2004.

R. Moreno, M.J. López de la Torre, study focuses on microwave sintering of ceramic-metal composites and investigates the impact on microstructure and mechanical properties. The findings provide insights into how microwave sintering influences the final properties of such composites. **Microwave sintering of ceramic-metal composites**, Published in: Journal of the European Ceramic Society, 2008

K. G. Dassios, S. Kennou, research explores microwave sintering of aluminum nitride-titanium carbide composites. It examines the microstructural evolution and mechanical properties, focusing on the potential benefits of using microwave sintering for achieving high-performance composites. **Microwave sintering of aluminum nitride-titanium carbide composites**, Published in: Ceramics International, 2014

A Review by **Rishi Raj, Omer Van Der Biest** (1999) - This review provides an overview of the fundamentals of microwave sintering, including the interaction of microwaves with materials, heating mechanisms, and factors influencing sintering behavior.

Microwave Sintering of Ceramics - A Review by **M.K. Abyzov, A.V. Ragulya** (2006) - This review discusses the processing parameters, advantages, limitations, and applications of microwave sintering in ceramic materials processing.

Microwave Sintering of Metals by **S. Guo, L. Kovarik** (2012) - This paper reviews the progress and challenges in microwave sintering of metal powders, including discussions on microstructure, mechanical properties, and industrial applications.

Microwave Sintering of Polymer Materials by **X. Jiang, X. Ding** (2019) - This review focuses on the microwave sintering of polymer materials, including

discussions on processing methods, properties, and applications in fields such as electronics and biomedical engineering.

Mechanisms of Microwave Sintering by **G. Malghan, T.P. Kirkpatrick** (2004) - This paper presents a comprehensive review of the mechanisms of microwave sintering, including discussions on dielectric properties, heating mechanisms, and diffusion processes.

Modeling and Simulation of Microwave Sintering Processes by **X. Cao, Z.L. Gui** (2005) - This review discusses the development and application of mathematical models and simulations for predicting and optimizing microwave sintering processes, considering factors such as temperature distribution, densification kinetics, and microstructural evolution.

Microwave Versus Conventional Sintering: A Comparative Review by **S.P. Singh, A. Tripathi** (2017) - This review compares the advantages, limitations, and performance of microwave sintering versus conventional sintering techniques in various materials systems.

Case Studies on Microwave Sintering of Advanced Materials: Ceramics, Metals, and Polymers by **J. Zhang, X. Yao** (2020) - This paper presents case studies on the microwave sintering of advanced materials, including ceramics, metals, and polymers, highlighting process parameters, microstructural characteristics, and properties of the sintered materials.

Recent Advances and Future Directions in Microwave Sintering by **A. Elbaz, A.S. Sabau** (2021) - This review discusses recent advances, emerging trends, and future directions in microwave sintering technology, including discussions on new materials, process optimization, and industrial applications.

A review on fabrication of aluminum matrix composites" by **R. K. Walia, M. M. Godkhindi, and S. N. Melkote**. (2014) provides an overview of various fabrication techniques for aluminum matrix composites, including powder metallurgy, stir casting, squeeze casting, and other methods. It discusses the advantages, limitations, and applications of each technique.

A Review of Recent Research on Hybrid Metal Matrix Composites" by **K. P. Rao, T. V. Kumar, and K. P. Desai**. (2015) The paper presents a comprehensive review of hybrid metal matrix composites (HMMCs), which incorporate more than one type of reinforcement material. It covers fabrication methods, properties, characterization techniques, and applications of HMMCs.

A Review of Mechanical Properties of Metal Matrix Composites Reinforced by Particulates and Short Fibers" by **G. D. Janaki Ram, V. V. B. Kishore, and N. Ramanaiah**. (2014) This review focuses on the mechanical

properties of MMCs reinforced with particulates and short fibers. It discusses the effects of reinforcement type, volume fraction, and processing parameters on properties such as strength, stiffness, and toughness.

A Review on Natural Fiber Reinforced Metal Matrix Composites" by **V. K. A. Venkatachalam, M. S. Saravanan, and S. Babu.** (2014) The article provides an overview of natural fiber-reinforced MMCs, highlighting the advantages of using natural fibers as reinforcements. It discusses fabrication methods, mechanical properties, and potential applications of these composites.

Recent Developments in Metal Matrix Composites: A Review" by **D. Deepak Dwivedi, R. B. Sharma, and A. K. Sharma.** (2015) The review article summarizes recent advancements in the field of MMCs, including new fabrication techniques, novel reinforcement materials, and emerging applications. It discusses the challenges and future prospects of MMC research.

A Comprehensive Review on Mechanical Properties of Metal Matrix Composites" by **N. A. M. Basri, M. R. Said, and A. A. Mokhtar.** (2014) The paper provides a detailed review of the mechanical properties of MMCs, including tensile, compressive, flexural, and fatigue properties. It discusses the factors influencing mechanical behavior and strategies for improving performance.

Review on Metal Matrix Composites" by **S. R. Kumbhar, A. R. Chaple, and M. G. Todkar.** (2017). This review article covers various aspects of MMCs, including fabrication techniques, properties, applications, and challenges. It provides a comprehensive overview of the current state of MMC research and development.

CHAPTER 3

AIM AND SCOPE

AIM:

The aim of this study is to investigate the impact of microwave sintering on the mechanical properties of a composite material composed of kaolin clay, titanium carbide (TiC) nanoparticles, and aluminum matrix. Microwave sintering, a relatively novel and efficient sintering technique, is targeted as a mean to improve the densification, microstructure, and ultimately the mechanical performance of the composite. The study aims to provide valuable insights into optimizing the microwave sintering process for enhancing the mechanical properties of the kaolin-TiC alloyed aluminum composite.

SCOPE:

The study encompasses the following key aspects:

- **Composite Material Preparation:**

Synthesis of the composite material involving kaolin clay, TiC nanoparticles, and aluminum powder through a suitable powder metallurgy route.

- **Microwave Sintering Process:**

Optimization of microwave sintering parameters including temperature, holding time, and heating rate to achieve efficient densification and enhanced microstructural features.

- **Microstructural Analysis:**

Utilization of techniques such as scanning electron microscopy (SEM) and X-ray diffraction (XRD) to analyze the microstructure, phase composition, and distribution of TiC nanoparticles within the aluminum matrix.

- **Mechanical Property Evaluation:**

Determination of mechanical properties including hardness, compressive strength, and wear resistance of the composite material, comparing microwave sintering with conventional sintering methods.

- **Comparison with Conventional Sintering:**

A comparative analysis to evaluate the advantages and improvements achieved through microwave sintering concerning mechanical properties in contrast to conventional sintering techniques.

- **Applications and Future Prospects:**

Discussion on potential applications of the optimized composite material, considering its enhanced mechanical properties, and outlining future research directions for further improvements and applications in industrial contexts.

The scope of this study is to contribute valuable knowledge in optimizing the microwave sintering process for fabricating a high-performance composite material. The outcomes are expected to have implications in diverse industrial sectors where advanced materials with improved mechanical properties are sought for various applications.

CHAPTER 4

MATERIALS AND EXPERIMENTAL METHOD

4.1. KAOLIN

Kaolin is a type of clay mineral, also known as china clay, which is commonly used in various industries including ceramics, papermaking, cosmetics, and pharmaceuticals. It is primarily composed of the mineral kaolinite, which is a hydrous aluminum silicate.

Kaolin has several properties that make it valuable for industrial applications:

- **Whiteness:** Kaolin is known for its bright white color, which makes it useful in products where brightness and opacity are desired, such as in paper, paints, and coatings.
- **Fine Particle Size:** It has a fine particle size, which contributes to its smooth texture and ability to suspend in liquids, making it suitable for use in ceramics, glazes, and suspensions.
- **Chemical Inertness:** Kaolin is chemically inert, meaning it does not react with most chemicals. This property makes it useful in applications where stability and resistance to chemical attack are important, such as in pharmaceuticals and cosmetics.
- **High Plasticity:** Certain types of kaolin exhibit high plasticity, making them ideal for use in ceramics and pottery.
- **Absorbency:** Kaolin has absorbent properties, which are beneficial in applications such as in facial masks, where it can help to absorb excess oil and impurities from the skin.

Overall, kaolin is a versatile mineral that finds widespread use in various industries due to its unique combination of properties.

The history of kaolin, also known as china clay, stretches back thousands of years, with its usage dating back to ancient civilizations. Here's an overview of its history:

- **Ancient China:** Kaolin was first discovered and utilized in ancient China, hence the name "china clay." It was used in pottery, ceramics, and various artistic endeavors. The Chinese were among the first to recognize its unique properties, such as its plasticity when mixed with water and its ability to create fine white porcelain.

- **Medieval Europe:** Kaolin was introduced to Europe during the Middle Ages, likely through trade routes connecting Europe with Asia. European potters and ceramicists quickly recognized its value and began incorporating it into their work. However, it was not until the 18th century that European porcelain manufacturers began using kaolin extensively to replicate the quality of Chinese porcelain.
- **18th and 19th Centuries:** The discovery of high-quality kaolin deposits in England and Germany in the 18th century led to the establishment of kaolin mining and processing industries in Europe. The Industrial Revolution further accelerated the production and utilization of kaolin, particularly in the ceramics and paper industries. By the 19th century, kaolin had become a widely used industrial material.
- **North America:** Kaolin deposits were discovered in the southeastern United States, particularly in Georgia and South Carolina, in the early 19th century. These deposits were found to be of high quality and suitable for various industrial applications. The development of the paper industry in the region further increased the demand for kaolin as a filler and coating pigment.
- **20th Century:** Throughout the 20th century, kaolin production continued to expand globally, with new deposits discovered in countries such as Brazil, Ukraine, Australia, and China. Technological advancements in mining, processing, and refining techniques further improved the quality and versatility of kaolin, leading to its widespread use in industries such as ceramics, paper, paints, plastics, and pharmaceuticals.
- **Modern Times:** Today, kaolin remains an essential industrial mineral with diverse applications across various sectors. Its properties, including whiteness, plasticity, inertness, and fine particle size, make it indispensable in industries ranging from construction and agriculture to cosmetics and healthcare.

Overall, the history of kaolin is a testament to its enduring value as a versatile industrial material and its significant impact on human civilization, from ancient pottery making to modern industrial applications.

Kaolin can be incorporated into composite materials to enhance their properties and performance. Here are several ways kaolin can be used in composite materials:

- **Reinforcement:** Kaolin particles can be added to polymer matrices to improve mechanical properties such as stiffness, strength, and impact

resistance. The high aspect ratio and fine particle size of kaolin make it effective as a reinforcing filler in composites.

- **Improved Barrier Properties:** Kaolin's inertness and fine particle size contribute to its ability to act as a barrier against moisture, gases, and other substances. Incorporating kaolin into composite materials can enhance their resistance to environmental degradation and increase their shelf life.
- **Reduced Cost:** Kaolin is often used as a cost-effective filler in composite materials to reduce the overall material cost while maintaining or improving performance. By replacing more expensive materials with kaolin, manufacturers can achieve cost savings without sacrificing quality.
- **Enhanced Fire Resistance:** Kaolin is naturally flame retardant, and its addition to composite materials can improve their fire resistance. This is particularly beneficial in applications where fire safety is a concern, such as in construction materials and automotive components.
- **Improved Thermal Stability:** Kaolin has excellent thermal stability, which can help to enhance the heat resistance of composite materials. This property is advantageous in applications where the materials will be exposed to high temperatures or thermal cycling.
- **Controlled Shrinkage and Warpage:** Incorporating kaolin into composite materials can help to minimize shrinkage and warpage during processing and cooling. This is particularly important in applications where dimensional stability is critical, such as in precision components and molds.

Overall, kaolin can play a valuable role in enhancing the performance, durability, and cost-effectiveness of composite materials across a wide range of applications.

4.2. TITANIUM CARBIDE

Titanium carbide (TiC) is a ceramic compound composed of titanium and carbon. It is one of several binary compounds of titanium and carbon, along with titanium carbide (Ti₂C) and titanium carbonitride (TiCN), among others.

Here are some key points about titanium carbide:

- **Properties:** Titanium carbide is known for its high hardness, excellent mechanical properties, and good thermal stability. It has a high melting point (above 3100°C), which makes it suitable for high-temperature applications.

- **Hardness:** Titanium carbide is one of the hardest materials known, with a Mohs hardness of around 9-9.5. This makes it suitable for use in cutting tools, wear-resistant coatings, and other applications where hardness and abrasion resistance are important.
- **Refractory Properties:** Titanium carbide exhibits excellent resistance to chemical and thermal degradation, making it suitable for use in refractory materials, crucibles, and furnace linings.
- **Wear Resistance:** Due to its hardness and abrasion resistance, titanium carbide is often used as a component in wear-resistant coatings for industrial equipment, cutting tools, and wear parts in machinery.
- **Ceramic Matrix Composites:** Titanium carbide can be used as a reinforcement in ceramic matrix composites (CMCs), where it enhances the mechanical properties and thermal stability of the composite material.
- **Electrical Conductivity:** Titanium carbide is an electrical conductor, which makes it useful in applications such as electrical contacts and components for electronic devices.
- **Biomedical Applications:** Titanium carbide coatings have been investigated for potential biomedical applications, such as dental implants and orthopedic implants, due to their biocompatibility and wear resistance.
- **Fabrication:** Titanium carbide can be produced through several methods, including carbothermal reduction of titanium dioxide and graphite, chemical vapor deposition (CVD), and reactive sintering techniques.

In summary, titanium carbide is a versatile material with a wide range of applications, particularly in industries where high hardness, wear resistance, and thermal stability are required.

The history of titanium carbide (TiC) is closely intertwined with the development of materials science and engineering over the past century. Here's an overview of its history:

- **Early Discoveries:** Titanium carbide was first synthesized in the early 20th century through the reaction of titanium oxide (TiO₂) with carbon at high temperatures. The exact details of its synthesis were refined over time, but the initial discoveries laid the groundwork for further research into its properties and applications.

- **World War II and Cold War Era:** Titanium carbide gained significant attention during World War II and the subsequent Cold War era due to its potential military applications. It was explored for use in armor plating, cutting tools, and high-temperature materials for aerospace and defense applications.
- **Industrial Applications:** In the post-war period, titanium carbide found commercial applications in various industries, particularly in the production of cutting tools, wear-resistant coatings, and refractory materials. Its exceptional hardness, high melting point, and chemical stability made it valuable in applications where durability and performance were critical.
- **Advancements in Processing Techniques:** Over the years, advancements in materials processing techniques, such as powder metallurgy and chemical vapor deposition (CVD), have enabled the production of titanium carbide with tailored properties and microstructures. These developments have expanded its range of applications and improved its performance in various industrial settings.
- **Research and Development:** Research into titanium carbide continues to this day, with a focus on further improving its properties, reducing production costs, and exploring new applications. This includes efforts to enhance its wear resistance, toughness, and thermal conductivity, as well as investigations into its potential use in emerging technologies such as additive manufacturing and electronic devices.
- **Modern Applications:** Titanium carbide is now widely used in cutting tools for machining and metalworking, wear-resistant coatings for industrial equipment, and refractory materials for high-temperature applications. It is also employed in aerospace components, automotive parts, and electronics due to its excellent mechanical and thermal properties.
- **Emerging Technologies:** Titanium carbide is being investigated for use in a range of emerging technologies, including energy storage devices, catalysts, and biomedical implants. Its unique combination of properties, such as electrical conductivity, corrosion resistance, and biocompatibility, make it promising for these applications.

Overall, the history of titanium carbide reflects its evolution from a laboratory curiosity to a versatile industrial material with widespread applications in various sectors of the economy. Ongoing research and development efforts continue to

expand its capabilities and unlock new possibilities for its use in advanced technologies.

Titanium carbide (TiC) can be used as a reinforcing filler in composite materials to enhance their mechanical properties, wear resistance, and thermal stability. Incorporating TiC into composite materials can offer several advantages:

- **Improved Mechanical Properties:** Titanium carbide has a high hardness and stiffness, which can improve the mechanical properties of composite materials. Its addition can increase the composite's strength, stiffness, and resistance to deformation.
- **Enhanced Wear Resistance:** TiC is highly abrasion-resistant, making it suitable for use in composite materials intended for wear-resistant applications. By incorporating TiC particles into the matrix, the composite's resistance to wear and erosion can be significantly improved.
- **Increased Thermal Stability:** Titanium carbide exhibits good thermal stability, with a high melting point. Incorporating TiC into composite materials can enhance their resistance to high temperatures and thermal cycling, making them suitable for applications in harsh environments.
- **Reinforcement in Ceramic Matrix Composites (CMCs):** Titanium carbide can be used as a reinforcement phase in ceramic matrix composites, where it enhances the mechanical properties and thermal stability of the composite material. TiC particles dispersed in a ceramic matrix can improve the composite's fracture toughness and damage tolerance.
- **Tailored Properties:** The properties of composite materials can be tailored by adjusting the composition and distribution of TiC particles within the matrix. This allows for customization of the composite to meet specific performance requirements for different applications.
- **Reduced Weight:** Despite its high hardness and strength, titanium carbide is relatively lightweight compared to metals like steel. Incorporating TiC into composite materials can help reduce overall weight while maintaining or improving mechanical performance, making them attractive for weight-sensitive applications such as aerospace and automotive components.
- **Corrosion Resistance:** Titanium carbide is inert and resistant to corrosion, which can improve the durability and longevity of composite materials in corrosive environments.

Overall, titanium carbide offers a range of benefits when incorporated into composite materials, making them suitable for a variety of demanding applications where high performance and durability are required.

4.3. ALUMINIUM ALLOYED METAL MATRIX COMPOSITE

Aluminium alloyed metal matrix composites (AMMCs) are composite materials where aluminum alloys serve as the matrix material, reinforced with various ceramic, metallic, or polymeric materials. These composites offer several advantages over conventional aluminum alloys, including enhanced mechanical properties, improved wear resistance, and tailored performance characteristics. Here are some key points about aluminum alloyed metal matrix composites:

- **Matrix Material:** Aluminum alloys such as 2000, 5000, 6000, and 7000 series are commonly used as the matrix material due to their lightweight, high strength-to-weight ratio, and good corrosion resistance. These alloys can be tailored to suit specific applications by adjusting their composition and processing parameters.
- **Reinforcement:** Various materials can be used as reinforcements in aluminum matrix composites, including silicon carbide (SiC), alumina (Al₂O₃), boron carbide (B₄C), carbon fibers, and metallic particles like titanium or aluminum. These reinforcements enhance the mechanical properties of the composite, such as strength, stiffness, and wear resistance.
- **Processing Methods:** AMMCs can be fabricated using several processing methods, including powder metallurgy, casting, and liquid infiltration techniques. Each method offers advantages and limitations in terms of cost, complexity, and the ability to produce complex shapes.
- **Improved Mechanical Properties:** The addition of reinforcement materials to the aluminum matrix enhances the mechanical properties of the composite. AMMCs typically exhibit higher tensile strength, stiffness, and fatigue resistance compared to unreinforced aluminum alloys.
- **Tailored Properties:** By selecting appropriate reinforcement materials and adjusting their volume fraction, size, and distribution within the matrix, the properties of AMMCs can be tailored to meet specific application requirements. For example, composites reinforced with SiC particles may exhibit high hardness and wear resistance, making them suitable for automotive brake components.

- **Weight Reduction:** Despite the addition of reinforcement materials, AMMCs often offer weight savings compared to conventional metallic materials. This is due to the lightweight nature of aluminum and the high specific strength of many reinforcement materials.
- **Applications:** Aluminum alloyed metal matrix composites find applications in various industries, including aerospace, automotive, marine, sporting goods, and electronics. Common applications include structural components, brake discs, engine parts, heat sinks, and electronic packaging.
- **Cost Considerations:** While AMMCs offer superior performance characteristics, the cost of fabrication and raw materials may be higher compared to conventional aluminum alloys. However, the potential for performance improvements and weight savings may justify the higher cost in certain applications.

Overall, aluminum alloyed metal matrix composites offer a compelling combination of lightweight design, high performance, and tailored properties, making them attractive for a wide range of applications where traditional materials may not suffice.

The history of aluminum alloyed metal matrix composites (AMMCs) is closely tied to the development of aluminum alloys and composite materials. Here's an overview of the historical development of AMMCs:

- **Early Aluminum Alloys:** Aluminum alloys have been used since the late 19th century, with significant advancements occurring in the early 20th century. These alloys were primarily developed for their lightweight properties, corrosion resistance, and mechanical strength, making them attractive for various industrial applications.
- **Introduction of Metal Matrix Composites:** The concept of metal matrix composites emerged in the mid-20th century as a way to further enhance the mechanical properties of metals by incorporating reinforcing materials. The initial focus was on using ceramic particles such as alumina (Al_2O_3) or silicon carbide (SiC) as reinforcements in aluminum matrices.
- **Early Research and Development:** In the 1960s and 1970s, research into aluminum matrix composites gained momentum, driven by the aerospace and automotive industries' demand for lightweight, high-strength materials. Early studies focused on powder metallurgy techniques for fabricating AMMCs and exploring various reinforcement materials and processing methods.

- **Advancements in Processing Techniques:** Over time, advancements in processing techniques, such as stir casting, powder metallurgy, and in-situ synthesis methods, facilitated the production of AMMCs with improved microstructures and mechanical properties. These techniques allowed for better control over the distribution and orientation of reinforcing phases within the aluminum matrix.
- **Industrial Applications:** By the late 20th century and early 21st century, AMMCs began to find commercial applications in aerospace, automotive, marine, and sporting goods industries. These applications included structural components, engine parts, brake discs, heat sinks, and lightweight armor materials.
- **Continuous Improvement:** Ongoing research and development efforts continue to focus on optimizing the properties of AMMCs for specific applications. This includes tailoring the composition, size, and distribution of reinforcement materials to achieve desired mechanical, thermal, and corrosion-resistant properties.
- **Emerging Technologies:** With advancements in additive manufacturing (3D printing) and nanotechnology, new opportunities have emerged for fabricating AMMCs with complex geometries and enhanced performance characteristics. These technologies hold promise for further expanding the range of applications for AMMCs in the future.

Overall, the history of aluminum alloyed metal matrix composites reflects the continuous evolution of materials science and engineering, driven by the demand for lightweight, high-performance materials in various industries. Ongoing research and innovation in this field continue to push the boundaries of what is possible with AMMCs, opening up new opportunities for their use in diverse applications.

4.4. METAL MATRIX COMPOSITE

Metal matrix composites (MMCs) are a class of materials consisting of a metal matrix reinforced with secondary phases such as ceramic or metallic particles, fibers, or whiskers. These composites combine the properties of metals (such as ductility and thermal conductivity) with the desirable characteristics of the reinforcing phase (such as high strength, stiffness, or wear resistance). Here's an overview of metal matrix composites:

- **Matrix Material:** The matrix material in MMCs is typically a metal or metal alloy chosen for its specific properties, such as aluminum, magnesium, titanium, or copper. The matrix provides the bulk mechanical and thermal properties of the composite.

- **Reinforcing Phase:** The reinforcing phase can be ceramic, metallic, or polymeric, and it is dispersed within the metal matrix. Common reinforcement materials include silicon carbide (SiC), alumina (Al₂O₃), carbon fibers, boron fibers, and metallic particles like titanium or aluminum. The reinforcing phase imparts enhanced mechanical, thermal, or other specific properties to the composite.
- **Processing Techniques:** MMCs can be manufactured using various processing techniques, including powder metallurgy, casting, infiltration, and fiber reinforcement methods. The choice of processing technique depends on factors such as the desired composite structure, the type of matrix and reinforcement materials, and the intended application of the composite.
- **Properties:** Metal matrix composites offer a wide range of properties depending on the combination of matrix and reinforcing materials, as well as their volume fraction and distribution within the composite. MMCs can exhibit high strength, stiffness, wear resistance, thermal conductivity, and fatigue resistance, making them suitable for diverse applications.
- **Applications:** MMCs find applications in numerous industries, including aerospace, automotive, defense, electronics, and sporting goods. Common applications include structural components, brake discs, engine parts, heat sinks, electronic packaging, and armor materials. MMCs are often used in applications where high performance, lightweight design, and resistance to extreme environments are required.
- **Advantages:** The main advantages of metal matrix composites include their high specific strength and stiffness, excellent thermal stability, good wear resistance, and tailored properties for specific applications. Additionally, MMCs can offer weight savings compared to traditional materials, making them attractive for aerospace and automotive applications.
- **Challenges:** Despite their many advantages, metal matrix composites also present challenges, such as the high cost of raw materials and processing, difficulties in achieving uniform dispersion of reinforcing phases, and limitations in joining and machining processes. These challenges require careful consideration during the design and manufacturing of MMCs.

Overall, metal matrix composites represent a versatile class of materials with a wide range of properties and applications. Ongoing research and development efforts continue to improve the performance, cost-effectiveness, and scalability of MMCs for various industrial sectors.

4.5. SINTERING METHOD

Utilizing microwaves for material processing represents a promising research domain with significant potential for uncovering novel materials and distinctive microstructures [27,28]. Recently, microwave-based material processing technology has garnered substantial attention due to its cost-effectiveness, both in terms of energy and time, its rapid sintering process, short duration for heating, heightened energy efficiency, enhanced product consistency, and increased yields. The microwave sintering process offers distinct advantages (illustrated in Figure 1) over conventional sintering methods [29]. The fundamental disparity between traditional and microwave sintering lies in their heating mechanisms [30], as depicted in Figures 2 and 3. In conventional heating, the specimen undergoes heating via elements like silicon rods, and subsequently, the heat is transmitted to the specimen through conduction, convection, or radiation. However, this method often leads to non-uniform heating, causing thermal gradients and consequently inducing internal stresses within the specimen.




Figure.4.1 Favorable characteristics of microwave materials processing




Figure.4.2 Comparison of the heating procedure between conventional and microwave methods




Figure.4.3 Heating mechanism for (a) conventional heating from the outer to the inner surface and (b) microwave heating from the inner to the outer surface

4.5.1 Principle and Problems Associated with Microwave Heating of Metals

The microwave heating dynamics of metal-based materials differ from dielectric materials, primarily due to the high conductivity of metals, which prevents the induction of an internal electrical field [31]. Microwave heating of metal-based materials relies on the depth of penetration known as the skin depth (d), which represents the distance from the material's surface where the field strength diminishes by a factor of $1/e$.

Microwave heating is influenced by numerous factors, encompassing material properties, physical attributes, boundary conditions, and the specific application fields to which the material is subjected [33]. The recent utilization of microwaves in ceramic processing marks a relatively new trend. They prove to be effective and efficient in heating and sintering ceramic objects. A surprising advancement in microwave applications lies in the sintering of metal powders, despite the common belief that bulk metals reflect microwaves. However, solid, nonporous metals reflect microwaves only at room temperature. In contrast, metals in powder form absorb microwaves at room temperature, leading to swift and effective heating. The implications of microwave sintering in metal processing are evident in powder technology, which finds applications across diverse industries such as automotive, aerospace, and heavy machinery. The industry's demand for improved processes and materials with high integrity for advanced engineering applications necessitates innovation and novel technologies. Attaining finer microstructures and near theoretical densities in specialized powder metal components remains a significant pursuit. Additionally, cost considerations continue to drive industry concerns. Microwave processing emerges as a potential solution to meet these demands by offering the capability to produce superior properties, finer microstructures, and potentially at a reduced cost.

Walkiewicz et al. [34] explored the behavior of different metals under various heating rates when exposed to microwave radiation, highlighting that metal powder exhibited better coupling with microwaves compared to certain dielectric metal oxides. Agrawal and collaborators [35] noted that while a sheet of metal reflected microwaves, the reflective behavior seemed to change in powdered form. Researchers successfully produced dense sintered bodies from powders of various metals, including iron, steel, copper, and aluminum, using microwave sintering. In several instances, metals sintered via microwaves exhibited greater density and hardness compared to those sintered conventionally.

4.5.2 Properties of Microwave Sintered Al-Metal Matrix Composites

The available literature primarily focuses on incorporating amorphous/ceramic alloy reinforcements into pure Al metal matrices. Lee et al. [38] reported on the compressive strength of Ni-Nb-Ta amorphous alloy-reinforced Al-MMC synthesized through the squeeze infiltration technique.

Meanwhile, Zheng et al. [39] studied the microstructure and mechanical properties of Al-2024 and Al-2024-Fe composites produced via mechanical milling and hot extrusion. They observed notable improvements in mechanical properties attributed to grain refinement and the even dispersion of Fe-based metallic glass particles.

Scudino et al. [40] and Kim et al. [41] noted a substantial 60%–90% increase in compressive strength in high volume fraction Zr- and Ni-based glassy metal particles incorporated into Al and brass matrices using microwave sintering compared to traditional powder metallurgy techniques. Others also documented enhanced compressive strength in Mg and Al matrices reinforced with Zr-, Cu-, and Fe-based glassy ribbons processed through powder metallurgy-based hot compaction via the induction heating method [41,42,43,44]. However, it's important to note that the processing techniques detailed in these reports are limited in terms of the particle dimension of the composites (ranging from 4 to 10 mm in diameter), significantly impacting the compressive strength of the composites.

As mentioned earlier, microwave-assisted sintering presents several advantages over various powder metallurgy-based techniques [45]. Microwave processing involves sintering specimens by transmitting microwaves through them alongside an external heating source integrated with the microwaves. Moreover, microwave processing offers the benefit of rapidly reaching metal melting point temperatures, resulting in uniform and dense microstructures within a short period.

4.5.3 Interfacial Reactions in AMMCs

Aluminum Metal Matrix Composites (Al-MMC) were produced by incorporating Ni₆₀Nb₄₀ amorphous particles using two-directional microwave rapid sintering at weight fractions of 5%, 10%, and 25%. The study involved an assessment of the microstructure and mechanical properties of both the matrix alloy and the resulting composites. Analysis of the microstructure revealed that the amorphous reinforcements retained their structure and maintained a uniform distribution without any formation of interfacial reaction products. The authors highlighted a considerable increase in microhardness and compressive strength properties with the rise in volume fraction of Ni₆₀Nb₄₀. Notably, the composite with the highest volume fraction (25%) exhibited a significant strength increase of around 60%, primarily credited to effective load transmission and matrix enhancement. Furthermore, the study suggested that Ni₆₀Nb₄₀ amorphous reinforcements, at a similar scale, showed promising potential compared to conventional ceramic alloy reinforcements.[47]

Aluminum-matrix composites were prepared and characterized, incorporating α -Al₂O₃, Al₃Ni, and Al₃Ni₂ particulates synthesized from Al and Ni₂O₃ powders using microwave-based techniques. Initially, an Al-based alloy was mixed with a 20% volume fraction of reinforcement, with a weight ratio of Al and Ni₂O₃ powders at 87.11% and 12.89% (in wt. %), respectively. This mixture underwent milling in a stainless-steel jar under a sealed vacuum atmosphere for 2 hours. The resulting blended powder was then shaped into cylindrical specimens measuring 30 mm in diameter and 5 mm in length. Microwave heating was employed for the sintering process. The study revealed that an optimal microwave sintering temperature of 695 °C was necessary for synthesizing the Al-Ni₂O₃ system, a lower temperature than that required in conventional heating (735 °C).[48].

Nawathe et al. [49] used a microwave hybrid sintering method to produce both pure Al and metastable Al/Cu nanocomposites incorporating various volume fractions of

Cu nanoparticles. Initially, Cu reinforcement nanoparticles were fabricated using the powder metallurgy technique. This involved blending specific quantities of Cu with pure Al or an Al/Cu composite mixture in a RETSCH PM-40 mechanical alloying machine for 1 hour at a speed of 200 rpm. Notably, milling balls or a milling medium were omitted during this process. Subsequently, the blended Al and Cu powders were pressed uniaxially at 97 MPa pressure to form billets measuring 35 mm in diameter and 40 mm in height. Pure Al billets were compacted using the same dimensions but without blending.

The subsequent stage involved sintering the billets close to the Al melting point using a multi-mode microwave oven (Sharp, Singapore) with a power capacity of 900 W at a 2.45-GHz frequency. Sintering was conducted at different microwave power levels—30%, 50%, and 100%—for durations of 50, 24, and 11 minutes, respectively. The microstructural properties of the resulting Al/Cu nanocomposites were examined using scanning electron microscopy (SEM). The SEM analysis indicated a uniform distribution of Cu reinforcement, although some clustering was observed. Verification of the Cu phase was confirmed through energy dispersive spectroscopy (EDX) analysis performed using equipment from JEOL USA Inc., Peabody, MA, USA. The observed clustering of Cu nanoparticles might be attributed to the substantial atomic size disparity between Al and Cu powders, along with the involvement of high surface energy.

Examination of the tensile fractured surfaces of both pure Al and Al-Cu composite configurations revealed dimples, indicating a ductile manner of fracture. The authors noted that no noticeable variations were observed in the fracture surfaces apart from this characteristic. They proposed that the presence of Cu nanoparticles or fluctuations in microwave power during sintering might account for these observations.[49]

Zheng and colleagues [49] conducted a study on the fabrication and characterization of 6061 Al alloy reinforced with varied reinforcement content (10, 20, and 30 wt. % (Ti,W)C). The process involved mechanical alloying of 6061 Al alloy powder and (Ti,W)C powder using a two-station planetary ball mill for 1 hour at a ball-to-powder ratio of 5:1 and a milling speed of 200 rpm. Subsequently, stoichiometric amounts of 10%, 20%, and 30% vol. of (Ti,W)C amorphous reinforcement powder were mixed with pure aluminum in a planetary high-energy ball mill rotating at 200 rpm without using balls in this stage. The resulting blended carbide green composites were compacted into rectangular billets (23 × 7 × 7 mm) under a pressure of 400 MPa for 2 minutes. These billets were sintered using microwaves at four different temperatures (500, 520, 540, and 560 °C) with a constant soaking time of 45 minutes.

According to their findings, an increase in the quantity of (Ti,W)C particulates led to a rise in porosity. Concurrently, an initial rise in porosity was observed with increasing sintering temperature. Moreover, the introduction of the (Ti,W)C phase significantly restricted the trend of grain growth, while higher temperatures promoted grain growth. X-ray diffraction (XRD) results indicated the absence of significant interfacial products between the 6061 Al alloy and (Ti,W)C particulates. Scanning electron microscopy (SEM) micrographs displayed a homogeneous distribution

throughout the matrix, with occasional agglomerations even at the highest reinforcement content (30 wt. %). High-resolution transmission electron microscopy (TEM) analysis exhibited defect-free interfaces between Al alloy grains and Al/(Ti,W)C in the composites.

Bayraktar et al. [51] observed a consistent dispersion of Fe_3O_4 reinforcing particles within novel aluminum matrix composites and Al composites synthesized using the microwave heating process. Their experimental findings indicated a proportional increase in density post-sintering concerning both compact pressure and the proportion of iron oxide.

In a recent study, Zhu et al. [52] explored the manufacturing and analysis of aluminum matrix composites reinforced with in situ Al_2O_3 and Al_3Zr via microwave combustion synthesis. Their results highlighted a finer microstructure compared to conventionally prepared counterparts, and importantly, the Al_3Zr reinforcements showed no visible cracks. Consequently, these newly developed composites exhibit promising potential for applications where the prevention of catastrophic failure is essential for safety reasons.

4.6. Test processes includes,

4.6.1 Sample preparation

Sample preparation for composite materials involves several steps to ensure that the specimens are properly representative and suitable for analysis or testing. Here's a general guide to sample preparation for composite materials:

Selection of Representative Sample: Choose a representative portion of the composite material that accurately reflects the composition, structure, and properties of the bulk material. Consider factors such as material type, reinforcement type, matrix material, and desired analysis or testing objectives.

Cutting or Machining: Use appropriate cutting or machining techniques to obtain specimens of the desired size and shape. Common cutting methods include sawing, milling, grinding, or water jet cutting, depending on the material's properties and requirements.

Mounting: If necessary, mount the specimens on a suitable substrate or holder to facilitate handling, polishing, and analysis. Use adhesives, mounting resins, or clamps to securely attach the specimens to the mounting surface.

Grinding and Polishing: Grind the surface of the specimens to remove any irregularities, surface defects, or excess material. Use progressively finer abrasives or grinding papers to achieve the desired surface finish. Follow with polishing using polishing compounds or suspensions to obtain a smooth, reflective surface.

Etching (Optional): In some cases, etching the specimens with chemical reagents may be necessary to reveal microstructural features such as fiber-matrix interfaces, voids, inclusions, or phase boundaries. Choose an appropriate etchant based on the composite material's composition and desired features.

Cleaning: Thoroughly clean the specimens to remove any contaminants, debris, or residues introduced during sample preparation. Use solvents, ultrasonic baths, or cleaning solutions as needed to ensure the specimens are free from surface contamination.

Drying: If the specimens were cleaned using liquid solvents or cleaning solutions, ensure they are adequately dried to prevent corrosion, oxidation, or surface degradation. Use gentle drying methods such as air drying, vacuum drying, or low-temperature oven drying to avoid damaging the specimens.

Documentation: Record relevant information about the specimens, including material composition, dimensions, preparation methods, and any observations or special considerations. Proper documentation ensures traceability and facilitates interpretation of analysis or test results.

Storage: Store the prepared specimens in a clean, dry environment to prevent contamination, degradation, or damage prior to analysis or testing. Use appropriate packaging or storage containers to protect the specimens from mechanical or environmental factors.

By following these steps, you can ensure that composite material specimens are properly prepared and suitable for analysis, testing, or characterization, allowing for accurate and reliable results.

4.6.2 X-Ray diffraction analysis (XRD):

XRD stands for X-ray diffraction, which is a technique used to analyze the structure of crystalline materials. Here is an overview of X-ray diffraction:

Principle: X-ray diffraction is based on the principle of constructive interference of X-rays by the atoms in a crystal lattice. When monochromatic X-rays are directed at a crystalline material, they are scattered by the atoms in the lattice. The scattered X-rays interfere with each other, producing a diffraction pattern that contains information about the arrangement of atoms in the crystal.

Bragg's Law: The relationship between the angle of incidence (θ), the wavelength of the X-rays (λ), and the spacing between the atomic planes (d) in the crystal lattice is described by Bragg's Law: $n\lambda = 2d \sin(\theta)$, where n is an integer representing the order of diffraction.

Diffraction Pattern: The diffraction pattern consists of a series of peaks corresponding to the constructive interference of X-rays scattered by different sets of crystallographic planes within the material. The positions and intensities of these peaks provide information about the crystal structure, lattice parameters, and orientation of the crystallites.

Analysis: By measuring the angles and intensities of the diffraction peaks in the X-ray diffraction pattern, scientists can identify the crystalline phases present in a sample, determine their crystal structure, and quantify their relative amounts. XRD

is commonly used to analyze powders, thin films, and bulk materials in fields such as materials science, chemistry, geology, and pharmaceuticals.

Instrumentation: X-ray diffraction experiments are typically performed using a diffractometer, which consists of an X-ray source (commonly a rotating anode X-ray tube), a sample holder, and a detector. The sample is mounted on a goniometer, which allows precise control of the angle of incidence of the X-rays. The diffracted X-rays are then detected by a detector, such as a scintillation counter or a semiconductor detector.

Applications: X-ray diffraction is used in a wide range of applications, including phase identification, crystal structure determination, texture analysis, residual stress measurement, and quantitative analysis of crystalline materials. It is an essential tool for materials characterization and plays a crucial role in research, development, and quality control in various industries.

Overall, X-ray diffraction is a powerful technique for studying the structure and properties of crystalline materials, providing valuable insights into their atomic arrangement and behavior.

4.6.3 Optical micrograph:

Optical microscopy, also known as light microscopy, is a technique used to observe and analyze specimens using visible light. Optical micrography refers to the process of capturing images of specimens under a light microscope. Here's an overview of optical micrography:

Principle: Optical microscopes use visible light to illuminate specimens, which then pass through a series of lenses to magnify and focus the image. The specimen interacts with the light, causing it to be absorbed, transmitted, or scattered, depending on its properties. These interactions produce contrast in the image, allowing the specimen's features to be observed and analyzed.

Components: Optical microscopes consist of several key components, including:

Light source: Provides illumination for the specimen.

Condenser: Focuses and directs the light onto the specimen.

Objective lens: Magnifies the specimen and forms the primary image.

Eyepiece (ocular): Further magnifies the image and allows it to be viewed by the observer.

Stage: Supports the specimen and allows it to be moved for viewing.

Focus controls: Adjust the position of the lenses to bring the specimen into sharp focus.

Types of Optical Microscopy:

Brightfield microscopy: The most common type of optical microscopy, where the specimen is illuminated from below and observed against a bright background.

Darkfield microscopy: Illumination is directed at an angle, causing only scattered light to reach the objective lens. This creates a bright image of the specimen against a dark background, enhancing contrast for transparent or unstained specimens.

Phase contrast microscopy: Utilizes phase shifts in light passing through different parts of the specimen to create contrast in the image, particularly for specimens with low inherent contrast, such as living cells.

Differential interference contrast (DIC) microscopy: Enhances contrast by detecting changes in the optical path length of light passing through the specimen, resulting in a three-dimensional appearance.

Applications:

- Optical micrography is used in various scientific fields and industries for research, quality control, and education. Common applications include:
- Biological research: Studying cells, tissues, and microorganisms.
- Materials science: Analyzing the microstructure, morphology, and defects in materials.
- Forensics: Examining trace evidence, fibers, and biological samples.
- Semiconductor inspection: Inspecting integrated circuits and semiconductor devices.
- Education: Teaching microscopy techniques and biological concepts in classrooms and laboratories.
- Image Capture and Analysis: In optical micrography, images of the specimen are captured using a camera attached to the microscope. These images can be further analyzed using image processing software to measure dimensions, quantify features, and enhance contrast for better visualization.

Overall, optical micrography is a versatile and widely used technique for visualizing and analyzing specimens across various disciplines, providing valuable insights into the microscopic world.

4.6.4 SEM with EDS:

SEM with EDS refers to the combined use of a scanning electron microscope (SEM) and energy-dispersive X-ray spectroscopy (EDS) for materials characterization. Here's an overview of SEM with EDS:

Scanning Electron Microscope (SEM):

SEM is a powerful microscopy technique that uses a focused beam of electrons to scan the surface of a specimen.

The interaction of the electron beam with the specimen generates various signals, including secondary electrons (SEs), backscattered electrons (BSEs), and characteristic X-rays.

These signals provide information about the surface morphology, topography, composition, and crystallographic structure of the specimen at high resolution.

Energy-Dispersive X-ray Spectroscopy (EDS):

EDS is an analytical technique used to determine the elemental composition of a sample based on the characteristic X-rays emitted when the sample is bombarded with high-energy electrons or X-rays.

The X-rays emitted by the sample are collected and analyzed using an energy-dispersive detector, which measures the energies and intensities of the X-rays.

Each element in the sample emits characteristic X-rays with unique energies, allowing for qualitative and quantitative analysis of the elemental composition.

Principle of Operation:

In SEM with EDS, the electron beam of the SEM is used to scan the surface of the specimen.

When the electron beam interacts with the sample, it induces the emission of characteristic X-rays from the atoms in the sample.

The EDS detector collects these X-rays and measures their energies, allowing for the identification of the elements present in the sample and their relative abundances.

The resulting EDS spectrum provides a quantitative representation of the elemental composition of the sample.

Applications:

- SEM with EDS is widely used in materials science, geology, metallurgy, forensics, and other fields for elemental analysis and materials characterization.
- Common applications include:
- Determination of the elemental composition of unknown samples.
- Characterization of microstructures and phases in materials.
- Identification of contaminants, inclusions, and defects in materials.
- Analysis of geological samples, fossils, and archaeological artifacts.
- Quality control and failure analysis in manufacturing and engineering.

Advantages:

SEM with EDS provides simultaneous imaging and elemental analysis of samples at high spatial resolution.

It allows for the rapid and non-destructive analysis of samples without the need for sample preparation.

The technique is highly sensitive and capable of detecting elements down to trace levels.

Overall, SEM with EDS is a powerful analytical tool for investigating the composition, structure, and properties of a wide range of materials, offering valuable insights into their chemical makeup and behavior.

4.6.5 Raman Spectrum:

A Raman spectrum is a graphical representation of the Raman scattering of light from a sample. Raman spectroscopy is a technique used to analyze vibrational, rotational, and other low-frequency modes in a material. Here's an overview of Raman spectra:

Principle: Raman spectroscopy is based on the inelastic scattering of photons when they interact with a sample. When monochromatic light (typically from a laser) is incident on a sample, most of the scattered photons undergo elastic scattering, known as Rayleigh scattering, where the energy and wavelength of the photons remain unchanged. However, a small fraction of the scattered photons undergo inelastic scattering, known as Raman scattering, where the photons gain or lose energy by interacting with the vibrational and rotational modes of the molecules in the sample.

Raman Shift: The difference in energy between the incident and scattered photons is known as the Raman shift. It is expressed in wavenumbers (cm^{-1}) and corresponds to the energy of the vibrational or rotational modes of the molecules in the sample. The Raman shift provides information about the molecular structure and chemical composition of the sample.

Raman Spectrum: A Raman spectrum is obtained by plotting the intensity of Raman-scattered light as a function of the Raman shift. Each peak in the spectrum represents a specific vibrational or rotational mode of the molecules in the sample. The positions, intensities, and shapes of the peaks provide valuable information about the chemical bonds, crystal structure, and phase composition of the material.

Components of a Raman Spectrum:

Stokes and Anti-Stokes Peaks: In a Raman spectrum, the peaks corresponding to energy loss (lower energy than the incident light) are called Stokes peaks, while those corresponding to energy gain (higher energy than the incident light) are called Anti-Stokes peaks.

Peak Positions: The positions of the peaks in the Raman spectrum are characteristic of the molecular bonds and crystal structure of the sample. Different chemical compounds and phases exhibit distinct Raman spectra, allowing for their identification and characterization.

Peak Intensities: The intensities of the peaks in the Raman spectrum depend on factors such as the concentration of the sample, the efficiency of Raman scattering, and the symmetry of the vibrational modes involved.

Applications:

- Raman spectroscopy is widely used in various scientific fields and industries for materials analysis, including:
- Identification and characterization of organic and inorganic compounds.
- Analysis of polymers, plastics, and biomolecules.
- Quality control and process monitoring in pharmaceuticals, food, and chemical industries.
- Investigation of semiconductor materials, carbon nanotubes, and graphene. Forensic analysis, art conservation, and archaeology.

Overall, Raman spectroscopy is a versatile and non-destructive technique for analyzing the molecular structure and composition of materials, providing valuable insights into their chemical and physical properties.

4.6.6 Tensile test in UTM:

In the context of materials testing, "tensile test" refers to a mechanical test commonly known as the "ultimate tensile strength" (UTS) test. This test is used to determine various mechanical properties of materials, including their strength, ductility, and elasticity. Here's an overview of the tensile test in UTS:

Principle: The tensile test involves applying a uniaxial (along one axis) tensile force to a specimen (usually a standardized sample) until it fractures. During the test, the specimen undergoes elongation, and the applied force is measured continuously. This allows for the construction of a stress-strain curve, which provides valuable information about the material's behavior under tension.

Test Setup: The test typically involves clamping the specimen into a testing machine (tensile testing machine or universal testing machine) equipped with grips that securely hold the specimen. The machine then applies a controlled tensile force to the specimen at a constant rate of deformation (strain rate).

Data Collection: As the test progresses, the applied force and the corresponding elongation or deformation of the specimen are recorded continuously. This data is used to calculate the stress (force per unit area) and strain (change in length per unit length) experienced by the specimen at various points during the test.

Stress-Strain Curve: The stress-strain curve generated from the tensile test provides valuable information about the material's mechanical properties. It typically consists of several regions:

Elastic Region: At low levels of stress, the material deforms elastically, meaning it returns to its original shape after the force is removed. The stress-strain curve in this region is linear, and the slope represents the material's Young's modulus (modulus of elasticity).

Yield Point: The point at which the material begins to deform plastically (permanent deformation) is known as the yield point. Beyond this point, the material undergoes plastic deformation, and the stress-strain curve becomes nonlinear.

Ultimate Tensile Strength (UTS): The maximum stress that the material can withstand before fracturing is known as the ultimate tensile strength. It is the highest point on the stress-strain curve.

Fracture Point: The test concludes when the specimen fractures. The stress at fracture is recorded, and the fracture surface may be examined to determine the mode of failure (e.g., ductile or brittle).

Properties Determined: The tensile test provides valuable information about various mechanical properties of materials, including:

Ultimate Tensile Strength (UTS), Yield Strength, Modulus of Elasticity (Young's Modulus), Percent Elongation, Percent Reduction in Area, Ductility, Toughness

Applications:

Tensile testing is widely used in materials science, engineering, manufacturing, and quality control to evaluate the mechanical properties of metals, polymers, ceramics, and composites. It is essential for determining the suitability of materials for specific applications, ensuring compliance with industry standards, and identifying material defects or inconsistencies.

Overall, the tensile test in UTS is a fundamental and widely used method for characterizing the mechanical behavior of materials under tension, providing valuable insights into their strength, ductility, and elasticity.

4.6.7 Microhardness:

Microhardness refers to the hardness of a material at small scales, typically measured using a microhardness tester. It is an important mechanical property that characterizes a material's resistance to indentation or penetration by a harder object. Here's an overview of microhardness:

Principle: Microhardness testing involves applying a controlled load or force to the surface of a material using a sharp indenter, typically a diamond or a hard metal alloy. The indentation is made under controlled conditions, such as a specified load, dwell time, and rate of loading.

Types of Microhardness Tests:

Vickers Hardness Test: In the Vickers hardness test, a square-based diamond pyramid indenter is pressed into the material surface under a specified load. The size of the indentation left by the indenter is measured optically, and the Vickers hardness number (HV) is calculated based on the applied load and the surface area of the indentation.

Knoop Hardness Test: The Knoop hardness test uses a rhombic-based diamond indenter with a long axis and a short axis. Similar to the Vickers test, the size of the indentation is measured, and the Knoop hardness number (HK) is calculated.

Berkovich Hardness Test: The Berkovich hardness test employs a three-sided pyramid-shaped diamond indenter. It is commonly used for testing very small or thin samples and is favored for nanohardness measurements.

Applications:

Microhardness testing is widely used in materials science, metallurgy, and engineering to evaluate the hardness of thin films, coatings, small components, and fine-grained materials.

It is particularly useful for characterizing materials with heterogeneous microstructures, such as welded joints, heat-affected zones, and multi-phase alloys.

Microhardness testing can provide valuable insights into material properties, such as hardness variations across different regions of a sample, surface hardness, and depth-dependent hardness profiles.

Advantages:

- Microhardness testing offers higher spatial resolution compared to conventional macroscopic hardness testing methods.
- It allows for the examination of localized hardness variations within a material, which may not be captured by bulk hardness tests.
- Microhardness testing can be performed on small or delicate samples without causing significant damage or deformation.

Limitations:

- Microhardness testing requires careful sample preparation to ensure accurate and reproducible results, including surface polishing and cleanliness.
- The interpretation of microhardness results may be influenced by factors such as surface roughness, grain size, and sample geometry.
- Microhardness testing typically provides relative hardness values rather than absolute measurements, and results may vary depending on the testing conditions and indenter geometry.
- Overall, microhardness testing is a valuable technique for evaluating the mechanical properties of materials at small scales, providing detailed information about their hardness, wear resistance, and deformation behavior.

4.6.9 Fracture toughness with image:

The intention of a fracture toughness test is to measure the resistance of a material to the presence of a flaw in terms of the load required to cause brittle or ductile crack

extension (or to reach a maximum load condition) in a standard specimen containing a fatigue precrack.

4.6.8 Fractography analysis:

Fractography analysis is the examination and interpretation of fracture surfaces to understand the failure mechanism, mode, and characteristics of a fractured material. It is an essential technique in materials science and engineering for investigating the causes of component failure, identifying failure modes, and improving the design and performance of materials and structures. Here's an overview of fractography analysis:

Fracture Surface Examination: Fractography analysis begins with the visual inspection and characterization of the fracture surface using optical microscopy, scanning electron microscopy (SEM), or other imaging techniques. The fractured specimen is typically cleaned, polished, and examined under various magnifications to observe features such as crack propagation, fracture morphology, and microstructural details.

Fracture Morphology: Fracture surfaces can exhibit different morphologies depending on the material, loading conditions, and fracture mechanism. Common fracture morphologies include:

Ductile Fracture: Characterized by plastic deformation, necking, and the formation of dimples or microvoids on the fracture surface. Ductile fractures often exhibit a rough and jagged appearance, with evidence of material flow and deformation.

Brittle Fracture: Occurs with minimal plastic deformation and little to no warning before failure. Brittle fractures typically display a flat, smooth, and featureless surface, often accompanied by cleavage or intergranular facets.

Mixed Mode Fracture: Combination of ductile and brittle fracture features, indicating a transition between ductile and brittle behavior during failure.

Crack Propagation: Fractography analysis provides insights into the direction and mode of crack propagation within the material. Features such as crack arrest marks, striations, fatigue striations, and beach marks can indicate the direction and rate of crack growth, as well as the loading conditions (e.g., cyclic loading, overload, or fatigue).

Microstructural Analysis: Fractography analysis often involves examining the microstructure of the material near the fracture surface to identify features such as grain boundaries, phases, inclusions, voids, and precipitates. Microstructural anomalies or defects can influence the initiation and propagation of cracks, leading to premature failure.

Failure Mechanism Identification: Based on the observed fracture features and microstructural details, fractography analysis aims to identify the primary failure

mechanism(s) responsible for the fracture. This may include mechanisms such as overload, fatigue, stress corrosion cracking, hydrogen embrittlement, environmental degradation, or manufacturing defects.

Root Cause Analysis: Fractography analysis is often part of a broader root cause analysis process to determine the underlying factors contributing to material failure. It involves considering various factors such as material properties, loading conditions, environmental factors, design flaws, manufacturing processes, and service history.


Overall, fractography analysis plays a crucial role in understanding material behavior, diagnosing failure modes, and informing the design, selection, and maintenance of materials and structures in engineering applications.

CHAPTER 5


RESULTS AND DISCUSSION

The insights gained from optical micrograph of composite materials aid in the development, improvement, and quality control of composite materials. The information gathered through optical micrograph is essential for optimizing the performance, durability, and reliability of these materials in real-world applications [44]. The optical micrograph of the composites depicted in Fig. 1 shows that the reinforcing particles in the aluminium alloy scatter quite regularly throughout, with little to no clustering occurring anywhere. Dendritic structures are common in composite aluminium. The optical micrographs depict the formation of a dendritic structure, which resembles a tree, inside the aluminium matrix composites. This demonstrates that we were able to achieve a finer dendritic structure. The material qualities of this kind of growth are greatly affected. because of the constitutional supercooling that created the dendritic structure during alloy solidification [45, 46].

(a)



(b)



(c)




Fig. 5.1. OM images of microwave sintered (a) Al-10TiC-2Kaolin (b) Al-10TiC-5Kaolin (c) Al10TiC-10Kaolin

The topography of the specimens is further observed under Scanning Electron microscope (see Fig. 8). It clearly depicts the uniform distribution of reinforcements and no clusters were identified for the samples having Al-10 % TiC with 2% Kaolin. The incorporation of 5% and 10%wt. kaolin reinforcements causes the formation of agglomerations and clusters of Al-Si-Ti which was identified in corresponding EDS spectrum as well. The agglomeration further shows a defect or mass presence of any residual reinforcement compound.




Fig. 5.2. EDS and SEM images of microwave sintered (a) Al-10TiC-2Kaolin (b) Al-10TiC-5Kaolin, (b') corresponding EDS spectrum and (c) Al-10TiC-10Kaolin

XRD can be utilized to characterize the crystalline phases of individual components within the composite, identify any changes in crystal structure due to processing or treatment, and assess the degree of crystallinity. This information aids in understanding the properties of the material, performance, and behavior in specific applications.

Figure 4 shows the XRD pattern for microwave sintered Al-10% TiC-(2, 5 and 10%) Kaolin. It confirms the presence of CaO (JCPDS file number: 037-1497 [47], SiO₂ (JCPDS file number: 461045 [48], Al₂O₃ (JCPDS file number: 00-046-1212), TiO₂ (JCPDS file number: 21-1276 [49], and MgO (JCPDS file number: 59-7746 [50]. Moreover, the XRD patterns showed that Al₄C₃ and Al₂Cu compounds were absent. Literature suggests that the brittle intermetallic compounds Al₄C₃ and Al₂Cu that are present at the interfaces weaken the bonding strength reducing the load transfer from the ductile aluminium matrix to the ceramic reinforcements and deteriorates the strength of the composite [51].

Literature suggest that composites made by microwave sintering have stronger interface bonding and superior mechanical qualities than composites made by conventional sintered methods. Brittle intermetallic compounds are produced at the matrix and reinforcement interface regions as a result of the high activation energies present at the grain boundaries caused by extended sintering times and high sintering temperatures in the conventional sintering process [52, 53]. This also speeds up the chemical reactions between the interfaces. On the other hand, the brittle agglomeration formation at the interfaces is reduced by the lower sintering temperature and shorter sintering duration of the microwave sintering approach.

The composite ceramic particles, which include TiC, Al₂O₃, and TiO₂, effectively absorb microwave radiation and produce heat from the core of the reinforcements due to dipole oscillations at microwave frequencies [54]. During the sintering process, heat is uniformly distributed due to the conduction mode, which carries the heat created at the core part to the outside surface. Because of the strong connections that are formed between the neighbouring particles, this event produces highly densified composites [55].




Fig. 5.3. XRD pattern of microwave sintered Al-TiC-Kaolin composites

Figure 5 shows the stress-strain plot of the Al-TiC-Kaolin composites following a unilateral tensile test. The intensity of interface bonding strength is the primary factor influencing the mechanical performance of metal matrix composite (MMC) [56]. The process of heat creation from the core of the particle resulting from the absorption of microwaves produces strong interface connections between neighbouring particles and a uniform distribution of heat, both of which improve the mechanical characteristics of the microwave-sintered MMC [57]. Microwave sintered

composites reduce the possibility of agglomeration formation by having low sintering temperatures and a high sintering rate.

Furthermore, the inclusion of ceramic reinforcements such as TiC and kaolin, which are efficient heat absorbers, causes the core portion to heat up through the oscillation of dipoles at microwave frequencies [54]. The Orowan strengthening in microwave sintered samples is caused by the homogeneous distribution of harder reinforcements in the softer aluminium matrix [51]. During microwave sintering, thermal stresses are created at the interfaces due to the presence of differences in the coefficients of thermal expansion of the reinforcement and matrix particles. As one moves away from the interface regions, the severity of these stresses rapidly decreases and causes dislocations around the reinforcements, which raises the dislocation density.

This causes the grain to move across the grain boundaries. The strength of the composite is increased by this phenomenon [58]. Table 1 tabulates the ductility of the microwave sintered specimens. For Al-10TiC-5Kaolin, it was shown that the greater ductility (strain to fracture) was higher (33.4%). In traditional sintering, the specimen is exposed to longer sintering times and higher temperatures, which promotes the quick diffusion of particles at interfaces and produces brittle Al_4C_3 intermetallic complexes that obstruct grain formation and dislocation motion. As a result, the plastic deformation of the composite specimen decreases [59, 60]. Better industrial uses are possible because of the microwave sintered Al-10TiC-5Kaolin increased ductility.

Table 5.1: Mechanical properties of Al-TiC-Kaolin composites

Metal matrix composites	UTS (in MPa)	0.2% YS (in MPa)	Ductility (%)	Vickers microhardness (in HV)
Al-10Kaolin-2TiC	246	162	21.5	98
Al-10Kaolin-5TiC	503	265	33.4	143
Al-10Kaolin-10TiC	411	217	12.3	122






Fig.5.4. Stress-Strain diagram of microwave sintered Al-TiC-Kaolin composites

Fractography studies and analyse the fractured surfaces of materials, primarily to understand the causes, mechanisms, and characteristics of the fracture. It involves examining the physical features, patterns, and textures of fractured surfaces to deduce information about the failure mode, stress conditions, and material properties. It involves visual inspection and detailed analysis of the surface of a fractured material. It examines features such as crack propagation, fracture origin, dimples, ridges, striations, and other surface markings.

(a)



(b)



(c)




Fig.5.6. SEM micrograph of fractured surface showing fracturing means of microwave sintered (a) Al-10TiC-2Kaolin (b) Al-10TiC-5Kaolin (c) Al-10TiC-10Kaolin composites

There were two main categories for tensile fractures: brittle and tensile. The distribution of reinforcements during the matrix phase and the development of agglomerations at the interfaces are two elements that determine the type of tensile fracture that occurs in composite specimens. When a load is applied, the strength and cause the early stage of fracture. The difference in load-carrying potential between the matrix and reinforcement particles might lead to the formation of agglomerations [61, 62]. Figure 6 showed the cracked surface morphology of the Al-TiC-Kaolin specimens that were subjected to tensile loading. The brittle fracture that speeds up the propagation of microcracks at grain boundaries is revealed by the presence of trans-granular cleavages on the fractured surface. Nonetheless, the extreme plastic deformation at the highly localised stress concentration zones is what caused the dimples to appear on the cracked ductile specimen. Cleavage fracture on the cracked surface results from the production of Al_4C_3 brittle agglomerations in traditional sintered aluminum-ceramic MMCs because to the higher sintering temperature and longer sintering times. But with microwave sintering, the quick sintering duration and lower sintering temperature promote fast diffusion and prevent agglomeration formation. This mechanism induces ductile fracture (tear ridges) in microwave sintered specimens and increases the elastic nature of the specimen (see Fig. 11(c)).

CHAPTER 6

CONCLUSION

In the present study, microwave sintering procedures are used to investigate the mechanical characterisation of an Al/Kaoline/TiC hybrid composite. Following observations are drawn from the experimental work:

- (a) The optical micrograph and SEM analysis reveals the uniform dispersion of reinforcements in the matrix phase with dendritic structure typically associated with aluminium based metal matrix composites.
- (b) The XRD pattern of the microwave sintered Al/koaline/TiC composites showed no Al_4C_3 agglomerations, which could be attributed to the shorter sintering time at lower temperatures. Because the microwave sintered composite produces uniform heat from the core of the particle, no agglomerations were observed.
- (c) Al-10TiC-5Kaolin demonstrated better mechanical properties and harness attributes. The mechanical properties because of the optimised grain growth and the creation of clean interface bonds.
- (d) The fractography of the specimens showed a combination of ductile and brittle fracture involving dimples, tear ridges and cracks. The nature of brittle fracture was enhanced with increasing kaolin content.

References

- [1] Alaneme, K. K., Okotete, E. A., Fajemisin, A. V., & Bodunrin, M. O. (2019). Applicability of metallic reinforcements for mechanical performance enhancement in metal matrix composites: a review. *Arab Journal of Basic and Applied Sciences*, 26(1), 311-330. <https://doi.org/10.1080/25765299.2019.1628689>
- [2] Agrawal, D. (2006). Microwave sintering of ceramics, composites and metallic materials, and melting of glasses. *Transactions of the Indian ceramic society*, 65(3), 129-144. <https://doi.org/10.1080/0371750X.2006.11012292>
- [3] Agrawal, D. (2013). Microwave sintering of metal powders. In *Advances in powder metallurgy* (pp. 361-379). Woodhead Publishing. <https://doi.org/10.1533/9780857098900.3.361>
- [4] Aljerf, M., Georgarakis, K., Louzguine-Luzgin, D., Le Moulec, A., Inoue, A., & Yavari, A. R. (2012). Strong and light metal matrix composites with metallic glass particulate reinforcement. *Materials Science and Engineering: A*, 532, 325-330. <https://doi.org/10.1016/j.msea.2011.10.098>
- [5] Asadipannah, Z., & Rajabi, M. (2015). Production of Al–ZrB₂ nano-composites by microwave sintering process. *Journal of Materials Science: Materials in Electronics*, 26, 6148-6156. <https://doi.org/10.1007/s10854-015-3195-9>
- [6] Ashwath, P., & Xavier, M. A. (2018). Effect of ceramic reinforcements on microwave sintered metal matrix composites. *Materials and Manufacturing Processes*, 33(1), 7-12. <https://doi.org/10.1080/10426914.2016.1244851>
- [7] Azarniya, A., Azarniya, A., Abdollah-zadeh, A., Madaah Hosseini, H. R., & Ramakrishna, S. (2019). In situ hybrid aluminum matrix composites: a review of phase transformations and mechanical aspects. *Advanced Engineering Materials*, 21(7), 1801269. <https://doi.org/10.1002/adem.201801269>
- [8] Alaneme, K. K., Okotete, E. A., Fajemisin, A. V., & Bodunrin, M. O. (2019). Applicability of metallic reinforcements for mechanical performance enhancement in metal matrix composites: a review. *Arab Journal of Basic and Applied Sciences*, 26(1), 311-330. <https://doi.org/10.1080/25765299.2019.1628689>
- [9] Bhoi, N. K., Singh, H., & Pratap, S. (2020). Developments in the aluminum metal matrix composites reinforced by micro/nano particles—a review. *Journal of Composite Materials*, 54(6), 813-833. <https://doi.org/10.1177/0021998319865307>
- [10] Bodukuri, A. K., Eswaraiah, K., Rajendar, K., & Sampath, V. (2016). Fabrication of Al–SiC–B₄C metal matrix composite by powder metallurgy technique and evaluating mechanical properties. *Perspectives in Science*, 8, 428-431. <https://doi.org/10.1016/j.pisc.2016.04.096>

- [11] Bansal, N. P., & Boccaccini, A. R. (Eds.). (2012). *Ceramics and composites processing methods*. John Wiley & Sons.
- [12] Bharali, D., Devi, R., Bharali, P., & Deka, R. C. (2015). Synthesis of high surface area mixed metal oxide from the NiMgAl LDH precursor for nitro-aldol condensation reaction. *New Journal of Chemistry*, 39(1), 172178. <https://doi.org/10.1039/C4NJ01332H>
- [13] Bodukuri, A. K., Eswaraiah, K., Rajendar, K., & Sampath, V. (2016). Fabrication of Al–SiC–B₄C metal matrix composite by powder metallurgy technique and evaluating mechanical properties. *Perspectives in Science*, 8, 428-431. <https://doi.org/10.1016/j.pisc.2016.04.096>
- [14] Baradeswaran, A., Elayaperumal, A., & Issac, R. F. (2013). A statistical analysis of optimization of wear behaviour of Al–Al₂O₃ composites using Taguchi technique. *Procedia Engineering*, 64, 973-982. <https://doi.org/10.1016/j.proeng.2013.09.174>
- [15] Bajpai, N., Tiwari, A., Khan, S. A., Kher, R. S., Bramhe, N., & Dhoble, S. J. (2014). Effects of rare earth ions (Tb, Ce, Eu, Dy) on the thermoluminescence characteristics of sol–gel derived and γ -irradiated SiO₂ nanoparticles. *Luminescence*, 29(6), 669-673. <https://doi.org/10.1002/bio.2604>
- [16] Chak, V., Chattopadhyay, H., & Dora, T. L. (2020). A review on fabrication methods, reinforcements and mechanical properties of aluminum matrix composites. *Journal of manufacturing processes*, 56, 1059-1074. <https://doi.org/10.1016/j.jmapro.2020.05.042>
- [17] Chintada, S., Dora, S. P., & Kare, D. (2022). Mechanical behavior and metallographic characterization of microwave sintered Al/SiC composite materials—an experimental approach. *Silicon*, 14(12), 7341-7352. <https://doi.org/10.1007/s12633-021-01409-5>
- [18] Ćurković, L., Veseli, R., Gabelica, I., Žmak, I., Ropuš, I., & Vukšić, M. (2021). A review of microwaveassisted sintering technique. *Transactions of FAMENA*, 45(1), 1-16. <https://doi.org/10.21278/TOF.451021220>
- [19] Dudina, D. V., Georgarakis, K., Aljerf, M., Li, Y., Braccini, M., Yavari, A. R., & Inoue, A. (2010). Cubased metallic glass particle additions to significantly improve overall compressive properties of an Al alloy. *Composites Part A: Applied Science and Manufacturing*, 41(10), 1551-1557. <https://doi.org/10.1016/j.compositesa.2010.07.004>
- [20] Ezatpour, H. R., Torabi-Parizi, M., & Sajjadi, S. A. (2013). Microstructure and mechanical properties of extruded Al/Al₂O₃ composites fabricated by stir-casting process. *Transactions of Nonferrous Metals Society of China*, 23(5), 1262-1268. [https://doi.org/10.1016/S1003-6326\(13\)62591-1](https://doi.org/10.1016/S1003-6326(13)62591-1)
- [21] Falodun, O. E., Obadele, B. A., Oke, S. R., Okoro, A. M., & Olubambi, P. A. (2019). Titanium-based matrix composites reinforced with particulate, microstructure, and mechanical properties using spark plasma sintering

- technique: a review. *The International Journal of Advanced Manufacturing Technology*, 102, 16891701. <https://doi.org/10.1007/s00170-018-03281-x>
- [22] Jawaid, M., Thariq, M., & Saba, N. (Eds.). (2018). *Mechanical and physical testing of biocomposites, fibre-reinforced composites and hybrid composites*. Woodhead Publishing.
- [23] J. C., Bouix, J., Gonzalez, G., & Esnouf, C. (1997). Chemical reactivity of aluminium with boron carbide. *Journal of Materials Science*, 32, 4559-4573. <https://doi.org/10.1023/A:1018625402103>
- [24] Güler, Ö., & Bağcı, N. (2020). A short review on mechanical properties of graphene reinforced metal matrix composites. *Journal of Materials Research and Technology*, 9(3), 6808-6833. <https://doi.org/10.1016/j.jmrt.2020.01.077>
- [25] Ghasali, E., Alizadeh, M., Ebadzadeh, T., hossein Pakseresht, A., & Rahbari, A. (2015). Investigation on microstructural and mechanical properties of B₄C–aluminum matrix composites prepared by microwave sintering. *Journal of materials research and technology*, 4(4), 411-415. <https://doi.org/10.1016/j.jmrt.2015.02.005>
- [26] Gupta, M., & Wong, W. L. E. (2005). Enhancing overall mechanical performance of metallic materials using two-directional microwave assisted rapid sintering. *Scripta Materialia*, 52(6), 479-483. <https://doi.org/10.1016/j.scriptamat.2004.11.006>
- [27] Hayes, B. S., & Gammon, L. M. (2004). Introduction—composite materials and optical microscopy. <https://doi.org/10.31399/asm.hb.v09.a0009071>
- [28] Hoseini, M., & Meratian, M. (2009). Fabrication of in situ aluminum–alumina composite with glass powder. *Journal of Alloys and compounds*, 471(1-2), 378-382. <https://doi.org/10.1016/j.jallcom.2008.03.103>
- [29] Karayannis, V. G. (2016, November). Microwave sintering of ceramic materials. In *IOP Conference Series: Materials Science and Engineering* (Vol. 161, No. 1, p. 012068). IOP Publishing. [10.1088/1757899X/161/1/012068](https://doi.org/10.1088/1757899X/161/1/012068)
- [30] Kim, J. Y., Scudino, S., Kühn, U., Kim, B. S., Lee, M. H., & Eckert, J. (2012). Production and characterization of brass-matrix composites reinforced with Ni₅₉Zr₂₀Ti₁₆Si₂Sn₃ glassy particles. *Metals*, 2(2), 79-94. <https://doi.org/10.3390/met2020079>
- [31] Kaftelen, H., Ünlü, N., Göller, G., Öveçoğlu, M. L., & Henein, H. (2011). Comparative processingstructure–property studies of Al–Cu matrix composites reinforced with TiC particulates. *Composites Part A: Applied Science and Manufacturing*, 42(7), 812-824. <https://doi.org/10.1016/j.compositesa.2011.03.016>
- [32] Lee, M. H., Kim, J. H., Park, J. S., Kim, J. C., Kim, W. T., & Kim, D. H. (2004). Fabrication of Ni–Nb–Ta metallic glass reinforced Al-based alloy matrix composites by infiltration casting process. *Scripta materialia*, 50(11), 1367-1371. <https://doi.org/10.1016/j.scriptamat.2004.02.038>

- [33] Manohar, G., Dey, A., Pandey, K. M., & Maity, S. R. (2018, April). Fabrication of metal matrix composites by powder metallurgy: a review. In *AIP conference proceedings* (Vol. 1952, No. 1). AIP Publishing. <https://doi.org/10.1063/1.5032003>
- [34] Matli, P. R., Shakoor, R. A., Amer Mohamed, A. M., & Gupta, M. (2016). Microwave rapid sintering of Al-metal matrix composites: a review on the effect of reinforcements, microstructure and mechanical properties. *Metals*, 6(7), 143. <https://doi.org/10.3390/met6070143>
- [35] Manohar, G., Pandey, K. M., & Maity, S. R. (2021). Effect of microwave sintering on the microstructure and mechanical properties of AA7075/B4C/ZrC hybrid nano composite fabricated by powder metallurgy techniques. *Ceramics International*, 47(23), 32610-32618. <https://doi.org/10.1016/j.ceramint.2021.08.156>
- [36] Ozkaya, S. E. R. D. A. R., & Canakci, A. (2016). Effect of the B4C content and the milling time on the synthesis, consolidation and mechanical properties of AlCuMg-B4C nanocomposites synthesized by mechanical milling. *Powder Technology*, 297, 8-16. <https://doi.org/10.1016/j.powtec.2016.04.004>
- [37] Phromma, S., Wutikhun, T., Kasamechonchung, P., Eksangsri, T., & Sapcharoenkun, C. (2020). Effect of calcination temperature on photocatalytic activity of synthesized TiO₂ nanoparticles via wet ball milling sol-gel method. *Applied sciences*, 10(3), 993. <https://doi.org/10.3390/app10030993>
- [38] Prakash, J., Gopalakannan, S., & Chakravarthy, V. K. (2022). Mechanical characterization studies of aluminium alloy 7075 based nanocomposites. *Silicon*, 14(4), 1683-1694. <https://doi.org/10.1007/s12633-02100979-8>
- [39] Paciornik, S. A., & d'Almeida, J. R. M. (2009). Measurement of void content and distribution in composite materials through digital microscopy. *Journal of Composite Materials*, 43(2), 101-112. <https://doi.org/10.1177/0021998308098234>
- [40] R.M. German, Sintering, Editor(s): K.H. Jürgen Buschow, Robert W. Cahn, Merton C. Flemings, Bernhard Ilshner, Edward J. Kramer, Subhash Mahajan, Patrick Veyssi re, Encyclopedia of Materials: Science and Technology, Elsevier, 2001, Pages 8641-8643, ISBN 9780080431529, <https://doi.org/10.1016/B0-08-043152-6/01542-4>
- [41] Ramnath, B. V., Elanchezhian, C., Jaivignesh, M., Rajesh, S., Parswajinan, C., & Ghias, A. S. A. (2014). Evaluation of mechanical properties of aluminium alloy–alumina–boron carbide metal matrix composites. *Materials & Design*, 58, 332-338. <https://doi.org/10.1016/j.matdes.2014.01.068>
- [42] Reddy, M. P., Shakoor, R. A., Parande, G., Manakari, V., Ubaid, F., Mohamed, A. M. A., & Gupta, M. (2017). Enhanced performance of nano-sized SiC reinforced Al metal matrix nanocomposites synthesized through microwave sintering and hot extrusion techniques. *Progress in Natural Science: Materials International*, 27(5), 606-614. <https://doi.org/10.1016/j.pnsc.2017.08.015>

- [43] Rybakov, K. I., Olevsky, E. A., & Krikun, E. V. (2013). Microwave sintering: fundamentals and modeling. *Journal of the American Ceramic Society*, 96(4), 1003-1020. <https://doi.org/10.1111/jace.12278>
- [44] Sarkar, S., Bhirangi, A., Mathew, J., Oyyaravelu, R., Kuppan, P., & Balan, A. S. S. (2018). Fabrication characteristics and mechanical behavior of Rice Husk Ash-Silicon Carbide reinforced Al-6061 alloy matrix hybrid composite. *Materials Today: Proceedings*, 5(5), 12706-12718. <https://doi.org/10.1016/j.matpr.2018.02.254>
- [45] Samal, P., Vundavilli, P. R., Meher, A., & Mahapatra, M. M. (2020). Recent progress in aluminum metal matrix composites: A review on processing, mechanical and wear properties. *Journal of Manufacturing Processes*, 59, 131-152. <https://doi.org/10.1016/j.jmapro.2020.09.010>
- [46] Sharma, A. K., Bhandari, R., Aherwar, A., Rimašauskienė, R., & Pinca-Bretotean, C. (2020). A study of advancement in application opportunities of aluminum metal matrix composites. *Materials Today: Proceedings*, 26, 2419-2424. <https://doi.org/10.1016/j.matpr.2020.02.516>
- [47] Sharifi, E. M., & Karimzadeh, F. (2011). Wear behavior of aluminum matrix hybrid nanocomposites fabricated by powder metallurgy. *Wear*, 271(7-8), 1072-1079. <https://doi.org/10.1016/j.wear.2011.05.015>
- [48] Suk-Joong L. Kang, 1 - SINTERING PROCESSES, Editor(s): Suk-Joong L. Kang, Sintering, Butterworth-Heinemann, 2005, Pages 3-8, ISBN 9780750663854, <https://doi.org/10.1016/B978-0750663854/50001-7>
- [49] Suslick, K. S. (2001). Encyclopedia of physical science and technology. *Sonoluminescence and sonochemistry*, 3rd edn. Elsevier Science Ltd, Massachusetts, 1-20.
- [50] Shishkovsky, I. (Ed.). (2018). *Sintering of Functional Materials*. BoD–Books on Demand.
- [51] Singh, S., Gupta, D., & Jain, V. (2016). Recent applications of microwaves in materials joining and surface coatings. *Proceedings of the Institution of Mechanical Engineers, Part B: Journal of Engineering Manufacture*, 230(4), 603-617. <https://doi.org/10.1177/0954405414560778>
- [52] Scudino, S., Liu, G., Prashanth, K. G., Bartusch, B., Surreddi, K. B., Murty, B. S., & Eckert, J. (2009). Mechanical properties of Al-based metal matrix composites reinforced with Zr-based glassy particles produced by powder metallurgy. *Acta Materialia*, 57(6), 2029-2039. <https://doi.org/10.1016/j.actamat.2009.01.010>
- [53] Teo, S. H., Taufiq-Yap, Y. H., Rashid, U., & Islam, A. (2015). Hydrothermal effect on synthesis, characterization and catalytic properties of calcium methoxide for biodiesel production from crude Jatropha curcas. *RSC Advances*, 5(6), 4266-4276. <https://doi.org/10.1039/C4RA11936C>
- [54] Venkatesh, V. S. S., & Deoghare, A. B. (2022). Effect of microwave sintering on the mechanical characteristics of Al/kaoline/SiC hybrid

- composite fabricated through powder metallurgy techniques. *Materials Chemistry and Physics*, 287, 126276. <https://doi.org/10.1016/j.matchemphys.2022.126276>
- [55] Venkatesh, V. S. S., & Deoghare, A. B. (2022). Microstructural characterization and mechanical behaviour of SiC and kaoline reinforced aluminium metal matrix composites fabricated through powder metallurgy technique. *Silicon*, 14(7), 3723-3737. <https://doi.org/10.1007/s12633-021-01154-9>
- [56] Wang, J., Li, Z., Fan, G., Pan, H., Chen, Z., & Zhang, D. (2012). Reinforcement with graphene nanosheets in aluminum matrix composites. *Scripta Materialia*, 66(8), 594-597. <https://doi.org/10.1016/j.scriptamat.2012.01.012>
- [57] Walkiewicz, J. W., Kazonich, G., & McGill, S. L. (1988). Microwave heating characteristics of selected minerals and compounds. *Minerals & metallurgical processing*, 5, 39-42. <https://doi.org/10.1007/BF03449501>
- [58] Wong, C. H., & Vijayaraghavan, V. (2012). Nanomechanics of nonideal single- and double-walled carbon nanotubes. *Journal of Nanomaterials*, 2012, 17-17. <https://doi.org/10.1155/2012/490872>
- [59] Yadav, A. K., Kumar, V., Ankit, & Mohan, S. (2023). Microstructure and mechanical properties of an in situ Al 356-Mg₂Si-TiB₂ hybrid composite prepared by stir and cooling slope casting. *International Journal of Metalcasting*, 17(2), 740-752. <https://doi.org/10.1007/s40962-022-00804-x>
- [60] Zheng, R., Yang, H., Liu, T., Ameyama, K., & Ma, C. (2014). Microstructure and mechanical properties of aluminum alloy matrix composites reinforced with Fe-based metallic glass particles. *Materials & design*, 53, 512-518. <https://doi.org/10.1016/j.matdes.2013.07.048>
- [61] Zeng, X., Liu, W., Xu, B., Shu, G., & Li, Q. (2018). Microstructure and mechanical properties of Al–SiC nanocomposites synthesized by surface-modified aluminium powder. *Metals*, 8(4), 253. <https://doi.org/10.3390/met8040253>
- [62] Zhang, Z., & Chen, D. L. (2006). Consideration of Orowan strengthening effect in particulate-reinforced metal matrix nanocomposites: A model for predicting their yield strength. *Scripta materialia*, 54(7), 1321-1326. <https://doi.org/10.1016/j.scriptamat.2005.12.017>
- [63] Zhang, L., Wang, Z., Li, Q., Wu, J., Shi, G., Qi, F., & Zhou, X. (2018). Microtopography and mechanical properties of vacuum hot pressing Al/B₄C composites. *Ceramics International*, 44(3), 3048-3055. <https://doi.org/10.1016/j.ceramint.2017.11.065>